



PFA 1500x1500x0,8 mm natur

Artikelnr P2202784

Beständig Delvis beständig Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxan	100	20 Å°C	
2-Hydroxypropionic Acid	90	20 Å°C	
Acetic Acid	100	20 Å°C	
Aceton	100	20 Å°C	
Ammoniak	â€”	20 Å°C	
Ammonium Chloride	â€”	20 Å°C	
Amyl Alcohol	â€”	20 Å°C	
Apple Juice	â€”	20 Å°C	
Bensen	â€”	20 Å°C	
Bleaching Solution	â€”	20 Å°C	
Boric Acid	100	20 Å°C	
Brake Fluid	â€”	20 Å°C	
Bränsle, aromatfritt	â€”	20 Å°C	
Butyl Acetate	â€”	20 Å°C	
Calcium Chloride	â€”	20 Å°C	
Carbon Disulfide	100	20 Å°C	
Carbon Tetrachloride	â€”	20 Å°C	
Citric Acid	10	20 Å°C	
Cyklohexanon	100	20 Å°C	
Cyklohexen	100	20 Å°C	
Diesel Fuel	â€”	20 Å°C	
Diethylene Oxide	â€”	20 Å°C	
Ethyl Acetate	100	20 Å°C	
Ethyl Alcohol	96	20 Å°C	
Ethylene Chloride	100	20 Å°C	
Fenol (vattenl.)	ca. 9	20 Å°C	
Food Oil	â€”	20 Å°C	

Kemikalie		Koncentration	Temp.	Beständighet
Formaldehyd (vattenl.)	40		20 Å°C	●
Formic Acid	10		20 Å°C	●
Frost Protection Agent	â€”		20 Å°C	●
Glycerin	100		20 Å°C	●
Glykol	100		20 Å°C	●
Heating Oil	â€”		20 Å°C	●
Heptan	100		20 Å°C	●
Hydrochloric Acid	10		20 Å°C	●
Hydrochloric Acid (concentrated)	â€”		20 Å°C	●
Hydrofluoric Acid	40		20 Å°C	●
Hydrogen Peroxide	10		20 Å°C	●
Hydrogen Sulfide (aqueous)	â€”		20 Å°C	●
Isopropyl Alcohol	100		20 Å°C	●
Klor (gas)	100		20 Å°C	●
Klorbensen	100		20 Å°C	●
Kloroform	â€”		20 Å°C	●
Kresol	â€”		20 Å°C	●
Linseed Oil	â€”		20 Å°C	●
Merkurokrom	â€”		20 Å°C	●
Methyl Alcohol	100		20 Å°C	●
Methyl Ethyl Ketone (MEK)	100		20 Å°C	●
Methylene Chloride	100		20 Å°C	●
Mineral Oils (aromatic free)	â€”		20 Å°C	●
Mj�lk	â€”		20 Å°C	●
Nitric Acid	10		20 Å°C	●
Nitric Acid (50%)	50		20 Å°C	●
Nitrobensen	â€”		20 Å°C	●
Oxalic Acid	â€”		20 Å°C	●
Ozone Gas	��� 0.5 ppm		20 Å°C	●
Paraffine Oil	100		20 Å°C	●
Perkloretylen	â€”		20 Å°C	●
Petroleum	100		20 Å°C	●
Petroleum Ether	100		20 Å°C	●
Phosphoric Acid	50		20 Å°C	●
Potassium Hydroxide liquor	50		20 Å°C	●

