



Artikelnr P2202795

Egenskap	Värde	Enhet	Standard
Densitet	2.15	g/cm³	DIN EN ISO 1183
Sträckgränspänning	15	MPa	DIN EN ISO 527
Elasticitetsmodul (drag)	450	MPa	DIN EN ISO 527
Brottspänning	24	MPa	DIN EN ISO 527
Brottåtgång	250	%	DIN EN ISO 527
Smältpunkt	300	°C	ISO 3146
Maximal drifttemperatur (korttid)	260	°C	
Maximal drifttemperatur	260	°C	
Minsta temperatur	-190	°C	
Värmeöverföringskoefficient (HDT/A)	75	°C	ISO 75
Dielektrisk styrka	33	kV/mm	DIN IEC 60243-1
Ytresistivitet	~10¹¹	Ω	DIN EN 61340
Termisk utvidningskoefficient	1.4	10⁻⁵ /K	ISO 11359-2
Hårldhet Shore D	55	° Shore D	DIN EN ISO 868

● Beständigt
 ● Delvis beständigt
 ● Ej beständigt

Kemikalie	Konc.	Resultat
1,4-Dioxan	100	
2-Hydroxypropionic Acid	90	
Acetic Acid	100	
Aceton	100	
Ammoniak	â€”	
Ammonium Chloride	â€”	
Amyl Alcohol	â€”	
Apple Juice	â€”	

Kemikalie	Konc.	Resultat
Bensen	â€”	●
Bleaching Solution	â€”	●
Boric Acid	100	●
Brake Fluid	â€”	●
Br��nsle, aromatfritt	â€”	●
Butyl Acetate	â€”	●
Calcium Chloride	â€”	●
Carbon Disulfide	100	●
Carbon Tetrachloride	â€”	●
Citric Acid	10	●
Cyklohexanon	100	●
Cyklohexen	100	●
Diesel Fuel	â€”	●
Diethylene Oxide	â€”	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Fenol (vattenl.)	ca. 9	●
Food Oil	â€”	●
Formaldehyd (vattenl.)	40	●
Formic Acid	10	●
Frost Protection Agent	â€”	●
Glycerin	100	●
Glykol	100	●
Heating Oil	â€”	●
Heptan	100	●
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	â€”	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	â€”	●
Isopropyl Alcohol	100	●
Klor (gas)	100	●
Klorbensen	100	●
Kloroform	â€”	●

Kemikalie	Konc.	Resultat
Kresol	â€”	●
Linseed Oil	â€”	●
Merkurokrom	â€”	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Mineral Oils (aromatic free)	â€”	●
Mj�lk	â€”	●
Nitric Acid	10	●
Nitric Acid (50%)	50	●
Nitrobensen	â€”	●
Oxalic Acid	â€”	●
Ozone Gas	� 0.5 ppm	●
Paraffine Oil	100	●
Perkloretylen	â€”	●
Petroleum	100	●
Petroleum Ether	100	�
Phosphoric Acid	50	�
Potassium Hydroxide liquor	50	�
Premium Fuel	â€”	�
Propyl Alcohol	â€”	�
Pyridin	â€”	�
Silicone Oil	â€”	�
Sodium Carbonate (aqueous)	â€”	�
Sodium Chloride (aqueous)	â€”	�
Sodium Hydrogen Sulfite	â€”	�
Sodium Hydroxide liquor	15	�
Sodium Hydroxide liquor (60)	60	�
Sodium Nitrate (aqueous)	â€”	�
Sodium Thiosulfate	â€”	�
Sulfuric Acid	96	�
Tetrahydrofuran (THF)	100	�
Toluen	100	�
Transformer Oil	â€”	�
Trikloret�n	100	�

Kemikalie	Konc.	Resultat
Vatten	â€”	●
Xylen	â€”	●
Ättika (standard)	5 - 10	●