

PMMA E 110/104x2000 mm transparent

Artikelnummer: P1200750

Kemisk beständighet

A Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

KEMIKALIE	BETYG	KONCENTRATION	TEMPERATUR
Aceton	not_resistant	100%%	
Ammoniak	resistant	conc.%	
Amylalkohol	not_resistant		
Bensen	not_resistant		
Bensin (premium)	not_resistant		
Bränsle, aromatfritt	resistant		
Butylacetat	not_resistant		
Citronsyra	resistant	10%%	
Cyklohexanon	not_resistant	100%%	
Cyklohexen	not_resistant	100%%	
Diesel	resistant		
Dietylenoxid	not_resistant		
Eldningsolja	resistant		
Etylacetat	not_resistant	100%%	
Etylalkohol (etanol)	resistant	96%%	
Etylenklorid	not_resistant	100%%	
Fenol, vattenl.	not_resistant	ca. 9%%	
Fluorvätesyra	not_resistant	40%%	
Formaldehyd, vattenl.	resistant	40%%	
Fosforsyra	not_resistant	50%%	
Glycerin	resistant	100%%	
Glykol	resistant	100%%	

KEMIKALIE	BETYG	KONCENTRATION	TEMPERATUR
Heptan	resistant	100%%	
Isopropylalkohol	resistant	100%%	
Kalciumklorid	resistant		
Kaliumhydroxidlösning	resistant	50%%	
Klorgas	partially_resistant	100%%	
Kloroform	not_resistant		
Koldisulfid	not_resistant	100%%	
Koltetraklorid	not_resistant		
Kresol	not_resistant		
Linolja	resistant		
Merkurokrom	not_resistant		
Metylalkohol (metanol)	not_resistant	100%%	
Metylenklorid	not_resistant	100%%	
Metyletylketon (MEK)	not_resistant	100%%	
Mineraloljor, aromatfria	resistant		
Mjök	resistant		
Myrsyra	not_resistant	10%%	
Natriumhydroxidlösning (natronlut)	resistant	15%%	
Natriumkarbonat, vattenl.	resistant		
Natriumklorid, vattenl.	resistant		
Natriumtiosulfat	resistant		
Natriumvätesulfit	resistant		
Natronlut (60%)	not_resistant	60%%	
Nitrobensen	not_resistant		
Oxalsyra	resistant		
Ozon (gas)	resistant	≤ 0.5 ppm%	
Paraffinolja	resistant	100%%	
Perkloretylen	partially_resistant		
Petroleum	partially_resistant	100%%	
Petroleumeter	resistant	100%%	
Salpetersyra	resistant	10%%	

KEMIKALIE	BETYG	KONCENTRATION	TEMPERATUR
Salpetersyra (50%)	not_resistant	50%%	
Saltsyra	resistant	10%%	
Saltsyra (konc.)	resistant	conc.%	
Silikonolja	resistant		
Svavelsyra	not_resistant	96%%	
Tetrahydrofuran (THF)	not_resistant	100%%	
Toluen	not_resistant	100%%	
Transformatorolja	resistant		
Trikloretan	not_resistant	100%%	
Vatten	resistant		
Väteperoxid	resistant	10%%	
Vätesulfid, vattenl.	resistant		
Xylen	not_resistant		
Äppeljuice	resistant		
Ättika, standard	resistant	5-10%%	
Ättiksyra	not_resistant	100%%	