

POM C 160/80x3000 mm svart

Artikelnummer: P1005766

Kemisk beständighet

A Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
1,4-Dioxan	good	100%%	
2-Hydroxipropionsyra (mjölksyra)	excellent	90%%	
Aceton	excellent	100%%	
Ammoniak	excellent	conc.%	
Ammoniumklorid	good		
Amylalkohol	excellent		
Bensen	good		
Bensin (premium)	excellent		
Blekningslösning	not_recommended	12.5 cl%	
Borsyra	good	100%%	
Bromsvätska	excellent		
Bränsle, aromatfritt	excellent		
Butylacetat	excellent		
Citronsyra	good	10%%	
Cyklohexanon	excellent	100%%	
Cyklohexen	excellent	100%%	
Diesel	excellent		
Dietylenoxid	excellent		
Eldningsolja	excellent		
Etylacetat	good	100%%	
Etylalkohol (etanol)	excellent	96%%	
Fenol, vattenl.	not_recommended	ca. 9%%	

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
Fluorvätesyra	not_recommended	40%%	
Formaldehyd, vattenl.	excellent	40%%	
Fosforsyra	not_recommended	50%%	
Frostskyddsmedel	excellent		
Glycerin	excellent	100%%	
Glykol	excellent	100%%	
Heptan	excellent	100%%	
Isopropylalkohol	excellent	100%%	
Kalciumklorid	excellent		
Kaliumhydroxidlösning	good	50%%	
Klorbensen	good	100%%	
Kloroform	not_recommended		
Koldisulfid	excellent	100%%	
Koltetraklorid	excellent		
Linolja	excellent		
Matolja	excellent		
Merkurokrom	not_recommended		
Metylalkohol (metanol)	excellent	100%%	
Metylenklorid	not_recommended	100%%	
Metyletylketon (MEK)	good	100%%	
Mineraloljor (aromatfria)	excellent		
Mjök	excellent		
Myrsyra	excellent	10%%	
Natriumkarbonat, vattenl.	excellent		
Natriumklorid, vattenl.	excellent		
Natriumnitrat, vattenl.	excellent		
Natriumvätesulfit	not_recommended		
Natronlut (15%)	excellent	15%%	
Natronlut (60%)	good	60%%	
Nitrobensen	good		
Oxalsyra	not_recommended		

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
Ozon (gas)	not_recommended	≤0.5 ppm%	
Paraffinolja	excellent	100%%	
Perkloretylen	excellent		
Petroleum	excellent	100%%	
Petroleometer	excellent	100%%	
Propylalkohol	excellent		
Salpetersyra	not_recommended	10%%	
Salpetersyra (50%)	not_recommended	50%%	
Saltsyra	not_recommended	10%%	
Saltsyra (konc.)	not_recommended	conc.%	
Silikonolja	excellent		
Svavelsyra	not_recommended	96%%	
Tetrahydrofuran (THF)	good	100%%	
Toluen	excellent	100%%	
Transformatorolja	excellent		
Trikloreten	good	100%%	
Vatten	excellent		
Väteperoxid	excellent	10%%	
Vätesulfid, vattenl.	excellent		
Xylen	excellent		
Äppeljuice	excellent		
Ättika, standard	excellent	5-10%%	
Ättiksyra	good	100%%	