

POM C FG 3000x620x50 mm natur

Artikelnummer: P1200837

Kemisk beständighet

A Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
1,4-Dioxan	partially_resistant	100%%	
2-Hydroxipropionsyra (mjölksyra)	resistant	90%%	
Aceton	resistant	100%%	
Ammoniak	resistant	conc.%	
Ammoniumklorid	partially_resistant		
Amylalkohol	resistant		
Bensen	partially_resistant		
Bensin (premium)	resistant		
Blekningslösning	not_resistant	12.5 cl%	
Borsyra	partially_resistant	100%%	
Bromsvätska	resistant		
Bränsle, aromatfritt	resistant		
Butylacetat	resistant		
Citronsyra	partially_resistant	10%%	
Cyklohexanon	resistant	100%%	
Cyklohexen	resistant	100%%	
Diesel	resistant		
Dietylenoxid	resistant		
Eldningsolja	resistant		
Etylacetat	partially_resistant	100%%	
Etylalkohol (etanol)	resistant	96%%	
Fenol, vattenl.	not_resistant	ca. 9%%	

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
Fluorvätesyra	not_resistant	40%%	
Formaldehyd, vattenl.	resistant	40%%	
Fosforsyra	not_resistant	50%%	
Frostskyddsmedel	resistant		
Glycerin	resistant	100%%	
Glykol	resistant	100%%	
Heptan	resistant	100%%	
Isopropylalkohol	resistant	100%%	
Kalciumklorid	resistant		
Kaliumhydroxidlösning	partially_resistant	50%%	
Klorbensen	partially_resistant	100%%	
Kloroform	not_resistant		
Koldisulfid	resistant	100%%	
Koltetraklorid	resistant		
Linolja	resistant		
Matolja	resistant		
Merkurokrom	not_resistant		
Metylalkohol (metanol)	resistant	100%%	
Metylenklorid	not_resistant	100%%	
Metyletylketon (MEK)	partially_resistant	100%%	
Mineraloljor (aromatfria)	resistant		
Mjök	resistant		
Myrsyra	resistant	10%%	
Natriumkarbonat, vattenl.	resistant		
Natriumklorid, vattenl.	resistant		
Natriumnitrat, vattenl.	resistant		
Natriumvätesulfit	not_resistant		
Natronlut (15%)	resistant	15%%	
Natronlut (60%)	partially_resistant	60%%	
Nitrobensen	partially_resistant		
Oxalsyra	not_resistant		

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
Ozon (gas)	not_resistant	≤0.5 ppm%	
Paraffinolja	resistant	100%%	
Perkloretylen	resistant		
Petroleum	resistant	100%%	
Petroleometer	resistant	100%%	
Propylalkohol	resistant		
Salpetersyra	not_resistant	10%%	
Salpetersyra (50%)	not_resistant	50%%	
Saltsyra	not_resistant	10%%	
Saltsyra (konc.)	not_resistant	conc.%	
Silikonolja	resistant		
Svavelsyra	not_resistant	96%%	
Tetrahydrofuran (THF)	partially_resistant	100%%	
Toluen	resistant	100%%	
Transformatorolja	resistant		
Trikloreten	partially_resistant	100%%	
Vatten	resistant		
Väteperoxid	resistant	10%%	
Vätesulfid, vattenl.	resistant		
Xylen	resistant		
Äppeljuice	resistant		
Ättika, standard	resistant	5-10%%	
Ättiksyra	partially_resistant	100%%	