



PlastShop.se
Söderleden 22
587 31 Linköping
Sverige



Kemisk beständighet
PlastShop.se • 2026-02-27

POM C FG 36/17x1000 mm svart

Artikelnummer: P1007018

Kemisk beständighet

A Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
1,4-Dioxane	B	100%%	
2-Hydroxypropionic Acid	A	90%%	
Acetic Acid	B	100%%	
Acetone	A	100%%	
Ammonia	A	conc.%	
Ammonium Chloride	B		
Amyl Alcohol	A		
Apple Juice	A		
Benzene	B		
Bleaching Solution	D	12.5 cl%	
Boric Acid	B	100%%	
Brake Fluid	A		
Butyl Acetate	A		
Calcium Chloride	A		
Carbon Disulfide	A	100%%	
Carbon Tetrachloride	A		
Chlorobenzene	B	100%%	
Chloroform	D		
	B		
Citric Acid		10%%	
Cyclohexanone	A	100%%	

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
Cyclohexene	A	100%%	
Diesel Fuel	A		
Diethylene Oxide	A		
Ethyl Acetate	B	100%%	
Ethyl Alcohol	A	96%%	
Food Oil	A		
Formaldehyde, aqueous	A	40%%	
Formic Acid	A	10%%	
Frost Protection Agent	A		
Fuel, aromatic free	A		
Glycerin	A	100%%	
Glycol	A	100%%	
Heating Oil	A		
Heptane	A	100%%	
Hydrochloric Acid	D	10%%	
Hydrochloric Acid (concentrated)	D	conc.%	
Hydrofluoric Acid	D	40%%	
Hydrogen Peroxide	A	10%%	
Hydrogen Sulfide, aqueous solution	A		
Isopropyl Alcohol	A	100%%	
Linseed Oil	A		
Mercurochrome	D		
Methyl Alcohol	A	100%%	
Methyl Ethyl Ketone (MEK)	B	100%%	
Methylene Chloride	D	100%%	
Milk	A		
Mineral Oils (aromatic free)	A		
Nitric Acid	D	10%%	
Nitric Acid (50%)	D	50%%	

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
Nitrobenzene	B		
Oxalic Acid	D		
Ozone Gas	D	≤0.5 ppm%	
Paraffine Oil	A	100%%	
Perchloroethylene	A		
Petroleum	A	100%%	
Petroleum Ether	A	100%%	
Phenol, aqueous	D	ca. 9%%	
Phosphoric Acid	D	50%%	
Potassium Hydroxide liquor	B	50%%	
Premium Fuel	A		
Propyl Alcohol	A		
Silicone Oil	A		
Sodium Carbonate, aqueous	A		
Sodium Chloride, aqueous	A		
Sodium Hydrogen Sulfite	D		
Sodium Hydroxide liquor (15%)	A	15%%	
Sodium Hydroxide liquor (60%)	B	60%%	
Sodium Nitrate, aqueous	A		
Sulfuric Acid	D	96%%	
Tetrahydrofuran, THF	B	100%%	
Toluene	A	100%%	
Transformer Oil	A		
Trichloroethylene	B	100%%	
Vinegar, standard	A	5-10%%	
Water	A		
Xylene	A		



PlastShop.se
Söderleden 22
587 31 Linköping
Sverige

<https://plastshop.se>

Informationen i detta dokument baseras på aktuell kunskap och erfarenhet. Värden kan variera beroende på bearbetning och användningsförhållanden. Alla uppgifter utan garanti.