Platta i POM H 3000x500x25 mm svart

Artikelnr P1008725

🟢 BestÃ¤ndig 🟡 Delvis bestÃ¤ndig 🔴 Ej bestÃ¤ndig

Kemikalie	Koncentration	Temp.	BestÃ¤ndighet
1,4-Dioxan	100%	20 Â°C	🟡
2-Hydroxypropionic Acid	90%	20 Â°C	🟢
Acetic Acid	100%	20 Â°C	🟡
Aceton	100%	20 Â°C	🟢
Ammoniak	conc.	20 Â°C	🟢
Ammonium Chloride	â€”	20 Â°C	🟡
Amyl Alcohol	â€”	20 Â°C	🟢
Apple Juice	â€”	20 Â°C	🟢
Bensen	â€”	20 Â°C	🟡
Bleaching Solution	12.5 cl	20 Â°C	🔴
Boric Acid	100%	20 Â°C	🟡
Brake Fluid	â€”	20 Â°C	🟢
BrÃ¤nsle, aromatfritt	â€”	20 Â°C	🟢
Butyl Acetate	â€”	20 Â°C	🟢
Calcium Chloride	â€”	20 Â°C	🟢
Carbon Disulfide	100%	20 Â°C	🟢
Carbon Tetrachloride	â€”	20 Â°C	🟢
Citric Acid	10%	20 Â°C	🟡
Cyklohexanon	100%	20 Â°C	🟢
Cyklohexen	100%	20 Â°C	🟢
Diesel Fuel	â€”	20 Â°C	🟢
Diethylene Oxide	â€”	20 Â°C	🟢
Ethyl Acetate	100%	20 Â°C	🟡
Ethyl Alcohol	96%	20 Â°C	🟢
Ethylene Chloride	100%	20 Â°C	🟢
Fenol, vattenl.	ca. 9%	20 Â°C	🔴
Food Oil	â€”	20 Â°C	🟢

Kemikalie	Koncentration	Temp.	BestÃ¤ndighet
Formaldehyd, vattenl.	40%	20 Â°C	🟢
Formic Acid	10%	20 Â°C	🟢
Frost Protection Agent	â€”	20 Â°C	🟢
Glycerin	100%	20 Â°C	🟢
Glykol	100%	20 Â°C	🟢
Heating Oil	â€”	20 Â°C	🟢
Heptan	100%	20 Â°C	🟢
Hydrochloric Acid	10%	20 Â°C	🔴
Hydrochloric Acid (concentrated)	conc.	20 Â°C	🔴
Hydrofluoric Acid	40%	20 Â°C	🔴
Hydrogen Peroxide	10%	20 Â°C	🟢
Hydrogen Sulfide, aqueous solution	â€”	20 Â°C	🟢
Isopropyl Alcohol	100%	20 Â°C	🟢
Klor (gas)	100%	20 Â°C	🟢
Klorbensen	100%	20 Â°C	🟡
Kloroform	â€”	20 Â°C	🔴
Kresol	â€”	20 Â°C	🟢
Linseed Oil	â€”	20 Â°C	🟢
Merkurokrom	â€”	20 Â°C	🔴
Methyl Alcohol	100%	20 Â°C	🟢
Methyl Ethyl Ketone (MEK)	100%	20 Â°C	🟡
Methylene Chloride	100%	20 Â°C	🔴
Mineral Oils (aromatic free)	â€”	20 Â°C	🟢
MjÃ¶lk	â€”	20 Â°C	🟢
Nitric Acid	10%	20 Â°C	🔴
Nitric Acid (50%)	50%	20 Â°C	🔴
Nitrobensen	â€”	20 Â°C	🟡
Oxalic Acid	â€”	20 Â°C	🔴
Ozone Gas	â‰¤0.5 ppm	20 Â°C	🔴
Paraffine Oil	100%	20 Â°C	🟢
Perkloretylen	â€”	20 Â°C	🟢
Petroleum	100%	20 Â°C	🟢
Petroleum Ether	100%	20 Â°C	🟢
Phosphoric Acid	50%	20 Â°C	🔴
Potassium Hydroxide liquor	50%	20 Â°C	🟡

Kemikalie	Koncentration	Temp.	BestÃ¤ndighet
Premium Fuel	â€”	20 Â°C	🟢
Propyl Alcohol	â€”	20 Â°C	🟢
Pyridin	â€”	20 Â°C	🟢
Silicone Oil	â€”	20 Â°C	🟢
Sodium Carbonate, aqueous	â€”	20 Â°C	🟢
Sodium Chloride, aqueous	â€”	20 Â°C	🟢
Sodium Hydrogen Sulfite	â€”	20 Â°C	🔴
Sodium Hydroxide liquor (15%)	15%	20 Â°C	🟢
Sodium Hydroxide liquor (60%)	60%	20 Â°C	🟡
Sodium Nitrate, aqueous	â€”	20 Â°C	🟢
Sodium Thiosulfate	â€”	20 Â°C	🟢
Sulfuric Acid	96%	20 Â°C	🔴
Tetrahydrofuran, THF	100%	20 Â°C	🟡
Toluen	100%	20 Â°C	🟢
Transformer Oil	â€”	20 Â°C	🟢
Trikloreten	100%	20 Â°C	🟡
Vatten	â€”	20 Â°C	🟢
Xylen	â€”	20 Â°C	🟢
Ã„ttika, standard	5-10%	20 Â°C	🟢

This document is for informational purposes only. Specifications may change without notice. Generated 2026-03-23