

Platta i PP-C 2440x1220x5 mm svart (skyddsfolie)

Artikelnr P2201548

● Beständig
 ● Delvis beständig
 ● Ej beständig

| Kemikalie | Koncentration | Temp. | Beständighet |
|-------------------------|---------------|--------|--------------|
| 1,4-Dioxan | 100 | 20 Å°C | ● |
| 2-Hydroxypropionic Acid | 90 | 20 Å°C | ● |
| Acetic Acid | 100 | 20 Å°C | ● |
| Aceton | 100 | 20 Å°C | ● |
| Ammoniak | â€” | 20 Å°C | ● |
| Ammonium Chloride | â€” | 20 Å°C | ● |
| Amyl Alcohol | â€” | 20 Å°C | ● |
| Apple Juice | â€” | 20 Å°C | ● |
| Bensen | â€” | 20 Å°C | ● |
| Bleaching Solution | â€” | 20 Å°C | ● |
| Boric Acid | 100 | 20 Å°C | ● |
| Brake Fluid | â€” | 20 Å°C | ● |
| Bränsle, aromatfritt | â€” | 20 Å°C | ● |
| Butyl Acetate | â€” | 20 Å°C | ● |
| Calcium Chloride | â€” | 20 Å°C | ● |
| Carbon Disulfide | 100 | 20 Å°C | ● |
| Carbon Tetrachloride | â€” | 20 Å°C | ● |
| Citric Acid | 10 | 20 Å°C | ● |
| Cyklohexanon | 100 | 20 Å°C | ● |
| Cyklohexen | 100 | 20 Å°C | ● |
| Diesel Fuel | â€” | 20 Å°C | ● |
| Diethylene Oxide | â€” | 20 Å°C | ● |
| Ethyl Acetate | 100 | 20 Å°C | ● |
| Ethyl Alcohol | 96 | 20 Å°C | ● |
| Ethylene Chloride | 100 | 20 Å°C | ● |
| Fenol, vattenl. | ca. 9 | 20 Å°C | ● |
| Food Oil | â€” | 20 Å°C | ● |

| Kemikalie | Koncentration | Temp. | Beständighet |
|------------------------------------|---------------|--------|--------------|
| Formaldehyd, vattenl. | 40 | 20 Å°C | ● |
| Formic Acid | 10 | 20 Å°C | ● |
| Frost Protection Agent | â€” | 20 Å°C | ● |
| Glycerin | 100 | 20 Å°C | ● |
| Glykol | 100 | 20 Å°C | ● |
| Heating Oil | â€” | 20 Å°C | ● |
| Heptan | 100 | 20 Å°C | ● |
| Hydrochloric Acid | 10 | 20 Å°C | ● |
| Hydrochloric Acid (concentrated) | â€” | 20 Å°C | ● |
| Hydrofluoric Acid | 40 | 20 Å°C | ● |
| Hydrogen Peroxide | 10 | 20 Å°C | ● |
| Hydrogen Sulfide, aqueous solution | â€” | 20 Å°C | ● |
| Isopropyl Alcohol | 100 | 20 Å°C | ● |
| Klor (gas) | 100 | 20 Å°C | ● |
| Klorbensen | 100 | 20 Å°C | ● |
| Kloroform | â€” | 20 Å°C | ● |
| Kresol | â€” | 20 Å°C | ● |
| Linseed Oil | â€” | 20 Å°C | ● |
| Merkurokrom | â€” | 20 Å°C | ● |
| Methyl Alcohol | 100 | 20 Å°C | ● |
| Methyl Ethyl Ketone (MEK) | 100 | 20 Å°C | ● |
| Methylene Chloride | 100 | 20 Å°C | ● |
| Mineral Oils (aromatic free) | â€” | 20 Å°C | ● |
| MjÅlk | â€” | 20 Å°C | ● |
| Nitric Acid | 50 | 20 Å°C | ● |
| Nitric Acid | 10 | 20 Å°C | ● |
| Nitrobensen | â€” | 20 Å°C | ● |
| Oxalic Acid | â€” | 20 Å°C | ● |
| Ozone Gas | â‰ƒ 0.5 ppm | 20 Å°C | ● |
| Paraffine Oil | 100 | 20 Å°C | ● |
| Perkloretylen | â€” | 20 Å°C | ● |
| Petroleum | 100 | 20 Å°C | ● |
| Petroleum Ether | 100 | 20 Å°C | ● |
| Phosphoric Acid | 50 | 20 Å°C | ● |
| Potassium Hydroxide liquor | 50 | 20 Å°C | ● |

| Kemikalie | Koncentration | Temp. | Best ndighet |
|---------------------------|---------------|-------|--------------|
| Premium Fuel |    | 20  C |   |
| Propyl Alcohol |    | 20  C |   |
| Pyridin |    | 20  C |   |
| Silicone Oil |    | 20  C |   |
| Sodium Carbonate, aqueous |    | 20  C |   |
| Sodium Chloride, aqueous |    | 20  C |   |
| Sodium Hydrogen Sulfite |    | 20  C |   |
| Sodium Hydroxide liquor | 15 | 20  C |   |
| Sodium Hydroxide liquor | 60 | 20  C |   |
| Sodium Nitrate, aqueous |    | 20  C |   |
| Sodium Thiosulfate |    | 20  C |   |
| Sulfuric Acid | 96 | 20  C |   |
| Tetrahydrofuran (THF) | 100 | 20  C |   |
| Toluen | 100 | 20  C |   |
| Transformer Oil |    | 20  C |   |
| Trikloretan | 100 | 20  C |   |
| Vatten |    | 20  C |   |
| Xylen |    | 20  C |   |
|  ttika, standard | 5 - 10 | 20  C |   |