



PLASTSHOP.SE

PlastShop.se
Söderleden 22
587 31 Linköping
Sverige



PLASTSHOP.SE

Komplett teknisk dokumentation

PlastShop.se • 2026-02-27

PP-H AlphaPlus Twin-Wall 3000x1000x58 mm, 54 mm web grå

Artikelnummer: P2201169

3. Kemisk beständighet

A Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

KEMIKALIE	BETYG	KONC.	TEMP.
1,4-Dioxane	B	100%	
2-Hydroxypropionic Acid	A	90%	
Acetic Acid	A	100%	
Acetone	A	100%	
Ammonia	A		
Ammonium Chloride	A		
Amyl Alcohol	A		
Benzene	B		
Bleaching Solution	B		
Boric Acid	A	100%	
Brake Fluid	A		
Butyl Acetate	B		
Calcium Chloride	A		
Carbon Disulfide	B	100%	
Carbon Tetrachloride	D		
Chlorine (gas)	D	100%	
Chlorobenzene	A	100%	
Chloroform	B		
Citric Acid	A	10%	



PLASTSHOP.SE

PlastShop.se
Söderleden 22
587 31 Linköping
Sverige

KEMIKALIE	BETYG	KONC.	TEMP.
Cresol	A		
Cyclohexanone	A	100%	
Cyclohexene	A	100%	
Diesel Fuel	A		
Diethylene Oxide	B		
Ethyl Acetate	A	100%	
Ethyl Alcohol	A	96%	
Ethylene Chloride	A	100%	
Food Oil	A		
Formaldehyde, aqueous	A	40%	
Formic Acid	A	10%	
Frost Protection Agent	A		
Fuel, aromatic free	A		
Glycerin	A	100%	
Glycol	A	100%	
Heating Oil	A		
Heptane	B	100%	
Hydrochloric Acid	A	10%	
Hydrochloric Acid (concentrated)	A		
Hydrofluoric Acid	A	40%	
Hydrogen Peroxide	A	10%	
Hydrogen Sulfide, aqueous solution	A		
Isopropyl Alcohol	A	100%	
Linseed Oil	A		
Mercurochrome	A		
Methyl Alcohol	A	100%	
Methyl Ethyl Ketone (MEK)	A	100%	
Methylene Chloride	B	100%	
Milk	A		



PLASTSHOP.SE

PlastShop.se
Söderleden 22
587 31 Linköping
Sverige

KEMIKALIE	BETYG	KONC.	TEMP.
Mineral Oils (aromatic free)	A		
Nitric Acid	A	10%	
Nitric Acid	D	50%	
Nitrobenzene	A		
Oxalic Acid	A		
Ozone Gas	D	≤ 0.5 ppm%	
Paraffine Oil	A	100%	
Perchloroethylene	B		
Petroleum Ether	A	100%	
Phenol, aqueous	A	ca. 9%	
Phosphoric Acid	A	50%	
Potassium Hydroxide liquor	A	50%	
Premium Fuel	A		
Propyl Alcohol	A		
Pyridine	A		
Silicone Oil	A		
Sodium Carbonate, aqueous	A		
Sodium Chloride, aqueous	A		
Sodium Hydrogen Sulfite	A		
Sodium Hydroxide liquor	A	15%	
Sodium Hydroxide liquor	A	60%	
Sodium Nitrate, aqueous	A		
Sodium Thiosulfate	A		
Sulfuric Acid	B	96%	
Tetrahydrofuran (THF)	B	100%	
Toluene	A	100%	
Transformer Oil	A		
Trichloroethylene	B	100%	
Vinegar, standard	A	5 - 10%	



PLASTSHOP.SE

PlastShop.se
Söderleden 22
587 31 Linköping
Sverige

KEMIKALIE	BETYG	KONC.	TEMP.
Water	A		
Xylene	D		

PlastShop.se
Söderleden 22, Linköping, Sverige

Tel: +46 13 328 94 00
info@plastshop.se
<https://plastshop.se>

Informationen i detta dokument baseras på aktuell kunskap och erfarenhet. Värden kan variera beroende på bearbetning och användningsförhållanden. Alla uppgifter utan garanti.