

Platta i PTFE 1200x1200x20 mm natur

Artikelnr P1201016

● Beständig ● Delvis beständig ● Ej beständig

| Kemikalie               | Koncentration | Temp. | Beständighet |
|-------------------------|---------------|-------|--------------|
| 1,4-Dioxan              | 100           | 20 °C | ●            |
| 2-Hydroxypropionic Acid | 90            | 20 °C | ●            |
| Acetic Acid             | 100           | 20 °C | ●            |
| Aceton                  | 100           | 20 °C | ●            |
| Ammoniak                | -             | 20 °C | ●            |
| Ammonium Chloride       | -             | 20 °C | ●            |
| Amyl Alcohol            | -             | 20 °C | ●            |
| Apple Juice             | -             | 20 °C | ●            |
| Bensen                  | -             | 20 °C | ●            |
| Bleaching Solution      | -             | 20 °C | ●            |
| Boric Acid              | 100           | 20 °C | ●            |
| Brake Fluid             | -             | 20 °C | ●            |
| Bränsle, aromatfritt    | -             | 20 °C | ●            |
| Butyl Acetate           | -             | 20 °C | ●            |
| Calcium Chloride        | -             | 20 °C | ●            |
| Carbon Disulfide        | 100           | 20 °C | ●            |
| Carbon Tetrachloride    | -             | 20 °C | ●            |
| Citric Acid             | 10            | 20 °C | ●            |
| Cyklohexanon            | 100           | 20 °C | ●            |
| Cyklohexen              | 100           | 20 °C | ●            |
| Diesel Fuel             | -             | 20 °C | ●            |
| Diethylene Oxide        | -             | 20 °C | ●            |
| Ethyl Acetate           | 100           | 20 °C | ●            |
| Ethyl Alcohol           | 96            | 20 °C | ●            |
| Ethylene Chloride       | 100           | 20 °C | ●            |
| Fenol (vattenl.)        | ca. 9         | 20 °C | ●            |

| Kemikalie                        | Koncentration | Temp. | Beständighet |
|----------------------------------|---------------|-------|--------------|
| Food Oil                         | -             | 20 °C | ●            |
| Formaldehyd (vattenl.)           | 40            | 20 °C | ●            |
| Formic Acid                      | 10            | 20 °C | ●            |
| Frost Protection Agent           | -             | 20 °C | ●            |
| Glycerin                         | 100           | 20 °C | ●            |
| Glykol                           | 100           | 20 °C | ●            |
| Heating Oil                      | -             | 20 °C | ●            |
| Heptan                           | 100           | 20 °C | ●            |
| Hydrochloric Acid                | 10            | 20 °C | ●            |
| Hydrochloric Acid (concentrated) | -             | 20 °C | ●            |
| Hydrofluoric Acid                | 40            | 20 °C | ●            |
| Hydrogen Peroxide                | 10            | 20 °C | ●            |
| Hydrogen Sulfide (aqueous)       | -             | 20 °C | ●            |
| Isopropyl Alcohol                | 100           | 20 °C | ●            |
| Klor (gas)                       | 100           | 20 °C | ●            |
| Klorbensen                       | 100           | 20 °C | ●            |
| Kloroform                        | -             | 20 °C | ●            |
| Kresol                           | -             | 20 °C | ●            |
| Linseed Oil                      | -             | 20 °C | ●            |
| Merkurokrom                      | -             | 20 °C | ●            |
| Methyl Alcohol                   | 100           | 20 °C | ●            |
| Methyl Ethyl Ketone (MEK)        | 100           | 20 °C | ●            |
| Methylene Chloride               | 100           | 20 °C | ●            |
| Mineral Oils (aromatic free)     | -             | 20 °C | ●            |
| Mjölk                            | -             | 20 °C | ●            |
| Nitric Acid                      | 10            | 20 °C | ●            |
| Nitric Acid (50%)                | 50            | 20 °C | ●            |
| Nitrobensen                      | -             | 20 °C | ●            |
| Oxalic Acid                      | -             | 20 °C | ●            |
| Ozone Gas                        | ≤ 0.5 ppm     | 20 °C | ●            |
| Paraffine Oil                    | 100           | 20 °C | ●            |
| Perkloretylen                    | -             | 20 °C | ●            |
| Petroleum                        | 100           | 20 °C | ●            |
| Petroleum Ether                  | 100           | 20 °C | ●            |
| Phosphoric Acid                  | 50            | 20 °C | ●            |

| Kemikalie                    | Koncentration | Temp. | Beständighet |
|------------------------------|---------------|-------|--------------|
| Potassium Hydroxide liquor   | 50            | 20 °C | <div></div>  |
| Premium Fuel                 | -             | 20 °C | <div></div>  |
| Propyl Alcohol               | -             | 20 °C | <div></div>  |
| Pyridin                      | -             | 20 °C | <div></div>  |
| Silicone Oil                 | -             | 20 °C | <div></div>  |
| Sodium Carbonate (aqueous)   | -             | 20 °C | <div></div>  |
| Sodium Chloride (aqueous)    | -             | 20 °C | <div></div>  |
| Sodium Hydrogen Sulfite      | -             | 20 °C | <div></div>  |
| Sodium Hydroxide liquor      | 15            | 20 °C | <div></div>  |
| Sodium Hydroxide liquor (60) | 60            | 20 °C | <div></div>  |
| Sodium Nitrate (aqueous)     | -             | 20 °C | <div></div>  |
| Sodium Thiosulfate           | -             | 20 °C | <div></div>  |
| Sulfuric Acid                | 96            | 20 °C | <div></div>  |
| Tetrahydrofuran (THF)        | 100           | 20 °C | <div></div>  |
| Toluen                       | 100           | 20 °C | <div></div>  |
| Transformer Oil              | -             | 20 °C | <div></div>  |
| Trikloreten                  | 100           | 20 °C | <div></div>  |
| Vatten                       | -             | 20 °C | <div></div>  |
| Xylen                        | -             | 20 °C | <div></div>  |
| Ättika (standard)            | 5 - 10        | 20 °C | <div></div>  |