

PA12 150x3000 mm svart

Artikelnummer: P1000275

Kemisk beständighet

A Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

KEMIKALIE	BETYG	KONCENTRATION	TEMPERATUR
1,4-Dioxan	partially_resistant	100%	
2-Hydroxiopropionsyra (mjölksyra)	not_resistant	90%	
Aceton	partially_resistant	100%	
Ammoniak	resistant	conc.%	
Ammoniumklorid	resistant		
Amylalkohol	partially_resistant		
Bensen	resistant		
Bensin (premium)	resistant		
Blekningslösning	not_resistant	12.5 cl%	
Borsyra	partially_resistant	100%	
Bromsvätska	resistant		
Bränsle (aromatfritt)	resistant		
Butylacetat	resistant		
Citronsyra	resistant	10%	
Cyklohexanon	resistant	100%	
Cyklohexen	partially_resistant	100%	
Diesel	resistant		
Dietylenoxid	resistant		
Eldningsolja	resistant		
Etylacetat	resistant	100%	
Etylalkohol (etanol)	partially_resistant	96%	
Etylenklorid	not_resistant	100%	

KEMIKALIE	BETYG	KONCENTRATION	TEMPERATUR
Fenol (vattenl.)	not_resistant	ca. 9%	
Fluorvätesyra	not_resistant	40%	
Formaldehyd (vattenl.)	partially_resistant	40%	
Fosforsyra	not_resistant	50%	
Glycerin	resistant	100%	
Glykol	resistant	100%	
Heptan	resistant	100%	
Isopropylalkohol	not_resistant	100%	
Kalciumklorid	resistant		
Kaliumhydroxidlösning	resistant	50%	
Klor (gas)	not_resistant	100%	
Klorbensen	partially_resistant	100%	
Kloroform	not_resistant		
Koldisulfid	resistant	100%	
Koltetraklorid	resistant		
Kresol	not_resistant		
Linolja	resistant		
Matolja	resistant		
Merkurokrom	not_resistant		
Metylalkohol (metanol)	not_resistant	100%	
Metylenklorid	not_resistant	100%	
Metyletylketon (MEK)	not_resistant	100%	
Mineraloljor (aromatfria)	resistant		
Mjök	resistant		
Myrsyra	partially_resistant	10%	
Natriumhydroxidlösning (natronlut)	resistant	15%	
Natriumkarbonat (vattenl.)	resistant		
Natriumklorid (vattenl.)	resistant		
Natriumnitrat (vattenl.)	resistant		
Natriumtiosulfat	resistant		
Nitrobensen	partially_resistant		

KEMIKALIE	BETYG	KONCENTRATION	TEMPERATUR
Oxalsyra	resistant		
Ozon (gas)	not_resistant	≤ 0.5 ppm%	
Paraffinolja	resistant	100%	
Perkloretylen	resistant		
Petroleum	resistant	100%	
Petroleometer	resistant	100%	
Propylalkohol	not_resistant		
Pyridin	partially_resistant		
Salpetersyra	not_resistant	50%	
Salpetersyra	not_resistant	10%	
Saltsyra	partially_resistant	10%	
Saltsyra (konc.)	not_resistant	conc.%	
Silikonolja	resistant		
Svavelsyra	not_resistant	96%	
Tetrahydrofuran (THF)	partially_resistant	100%	
Toluen	resistant	100%	
Transformatorolja	resistant		
Trikloretan	partially_resistant	100%	
Vatten	resistant		
Väteperoxid	not_resistant	10%	
Vätesulfid (vattenl.)	resistant		
Xylen	resistant		
Äppeljuice	resistant		
Ättika (standard)	resistant	5 - 10%	