



Rundstång i PA6 C 65x1000 mm svart

Artikelnr P1001602

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densitet	1.1	g/cm³	ISO 1183
Sträckgränspänning	75	MPa	ISO 527
Elasticitetsmodul (drag)	3500	MPa	ISO 527-2
Brottåjning	25	%	ISO 527-2
Smältpunkt	220	°C	ISO 3146
Maximal drifttemperatur (korttid)	170	°C	
Maximal drifttemperatur	105	°C	
Minsta temperatur	-30	°C	
Värmeåtvärngning (HDT/A)	80	°C	ISO 75-2
Dielektrisk styrka	25	kV/mm	IEC 60243-1
Volymresistivitet	10¹¹	Ω·cm	IEC 60093
Dielektrisk konstant (1 MHz)	3.2	-	IEC 60250
Dielektrisk konstant (100 Hz)	3.6	-	IEC 60250
Dielektrisk förlustfaktor (1 MHz)	0.0	-	IEC 60250
Dielektrisk förlustfaktor (100 Hz)	0.0	-	IEC 60250
Båghållfasthet	85	MPa	ISO 527-2
Termisk konduktivitet	0.29	W/(m·K)	DIN 52612
Ytresistivitet	10¹¹	Ω	IEC 60093
Jämförande krypsträmsindex (CTI)	600	V	IEC 60112
Fuktabsorption till mättnad	2.3	%	ISO 62
Vattenabsorption till mättnad	6.5	%	ISO 62
Skårad slagseghet (Charpy)	3.5	kJ/m²	ISO 179/1eA
Termisk utvidgningskoefficient	0.8	10⁻⁵/K	ISO 11359
Kultryckshårdhet	148.3	MPa	ISO 2039-1

2. Kemisk beständighet

Beständig Delvis beständig Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxan	100	
2-Hydroxypropionic Acid	90	
Acetic Acid	100	
Aceton	100	
Ammoniak	conc.	
Ammonium Chloride	â€”	
Amyl Alcohol	â€”	
Apple Juice	â€”	
Bensen	â€”	
Bleaching Solution	12.5 cl	
Boric Acid	100	
Brake Fluid	â€”	
Br�nsle (aromatfritt)	â€”	
Butyl Acetate	â€”	
Calcium Chloride	â€”	
Carbon Disulfide	100	
Carbon Tetrachloride	â€”	
Citric Acid	10	
Cyklohexanon	100	
Cyklohexen	100	
Diesel Fuel	â€”	
Diethylene Oxide	â€”	
Ethyl Acetate	100	
Ethyl Alcohol	96	
Ethylene Chloride	100	
Fenol (vattenl.)	ca. 9	
Food Oil	â€”	
Formaldehyd (vattenl.)	40	
Formic Acid	10	
Frost Protection Agent	â€”	
Glycerin	100	
Glykol	100	
Heating Oil	â€”	
Heptan	100	
Hydrochloric Acid	10	

Kemikalie	Konc.	Resultat
Hydrochloric Acid (concentrated)	conc.	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	â€”	●
Isopropyl Alcohol	100	●
Klor (gas)	100	●
Klorbensen	100	●
Kloroform	â€”	●
Kresol	â€”	●
Linseed Oil	â€”	●
Merkurokrom	â€”	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Mineral Oils (aromatic free)	â€”	●
Mj�lk	â€”	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobensen	â€”	●
Oxalic Acid	â€”	●
Ozone Gas	â‰‰ 0.5 ppm	●
Paraffine Oil	100	●
Perkloretylen	â€”	●
Petroleum	100	●
Petroleum Ether	100	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	â€”	●
Propyl Alcohol	â€”	●
Pyridin	â€”	●
Silicone Oil	â€”	●
Sodium Carbonate (aqueous)	â€”	●
Sodium Chloride (aqueous)	â€”	●
Sodium Hydrogen Sulfite	â€”	●
Sodium Hydroxide liquor	15	●

Kemikalie	Konc.	Resultat
Sodium Hydroxide liquor	60	
Sodium Nitrate (aqueous)	â€”	
Sodium Thiosulfate	â€”	
Sulfuric Acid	96	
Tetrahydrofuran (THF)	100	
Toluen	100	
Transformer Oil	â€”	
Trikloretan	100	
Vatten	â€”	
Xylen	â€”	
Ättika (standard)	5 - 10	