



Rundst ng i PA6.6 130x3000 mm natur

Artikelnr P1002006

● Beständigt ● Delvis beständigt ● Ej beständigt

Kemikalie	Koncentration	Temp.	Beskrivning
1,4-Dioxan	100	20 Å°C	⚠️
2-Hydroxypropionic Acid	90	20 Å°C	🔴
Acetic Acid	100	20 Å°C	✅
Aceton	100	20 Å°C	⚠️
Ammoniak	conc.	20 Å°C	✅
Ammonium Chloride	â€”	20 Å°C	✅
Amyl Alcohol	â€”	20 Å°C	⚠️
Apple Juice	â€”	20 Å°C	✅
Bensen	â€”	20 Å°C	✅
Bleaching Solution	12.5 cl	20 Å°C	🔴
Boric Acid	100	20 Å°C	⚠️
Brake Fluid	â€”	20 Å°C	✅
Br�nsle (aromatfritt)	â€”	20 Å°C	✅
Butyl Acetate	â€”	20 Å°C	✅
Calcium Chloride	â€”	20 Å°C	✅
Carbon Disulfide	100	20 Å°C	✅
Carbon Tetrachloride	â€”	20 Å°C	✅
Citric Acid	10	20 Å°C	✅
Cyklohexanon	100	20 Å°C	✅
Cyklohexen	100	20 Å°C	⚠️
Diesel Fuel	â€”	20 Å°C	✅
Diethylene Oxide	â€”	20 Å°C	✅
Ethyl Acetate	100	20 Å°C	✅
Ethyl Alcohol	96	20 Å°C	⚠️
Ethylene Chloride	100	20 Å°C	🔴
Fenol (vattenl.)	ca. 9	20 Å°C	🔴
Food Oil	â€”	20 Å°C	✅

Kemikalie	Koncentration	Temp.	Beständighet
Formaldehyd (vattenl.)	40	20 Å°C	
Formic Acid	10	20 Å°C	
Frost Protection Agent	â€”	20 Å°C	
Glycerin	100	20 Å°C	
Glykol	100	20 Å°C	
Heating Oil	â€”	20 Å°C	
Heptan	100	20 Å°C	
Hydrochloric Acid	10	20 Å°C	
Hydrochloric Acid (concentrated)	conc.	20 Å°C	
Hydrofluoric Acid	40	20 Å°C	
Hydrogen Peroxide	10	20 Å°C	
Hydrogen Sulfide (aqueous)	â€”	20 Å°C	
Isopropyl Alcohol	100	20 Å°C	
Klor (gas)	100	20 Å°C	
Klorbensen	100	20 Å°C	
Kloroform	â€”	20 Å°C	
Kresol	â€”	20 Å°C	
Linseed Oil	â€”	20 Å°C	
Merkurokrom	â€”	20 Å°C	
Methyl Alcohol	100	20 Å°C	
Methyl Ethyl Ketone (MEK)	100	20 Å°C	
Methylene Chloride	100	20 Å°C	
Mineral Oils (aromatic free)	â€”	20 Å°C	
MjÅlk	â€”	20 Å°C	
Nitric Acid	10	20 Å°C	
Nitric Acid	50	20 Å°C	
Nitrobensen	â€”	20 Å°C	
Oxalic Acid	â€”	20 Å°C	
Ozone Gas	â‰¥ 0.5 ppm	20 Å°C	
Paraffine Oil	100	20 Å°C	
Perkloretylen	â€”	20 Å°C	
Petroleum	100	20 Å°C	
Petroleum Ether	100	20 Å°C	
Phosphoric Acid	50	20 Å°C	
Potassium Hydroxide liquor	50	20 Å°C	

