



Rundst ng i PA6.6 85x3000 mm svart

Artikelnr P1001913

Best ndig Delvis best ndig Ej best ndig

Kemikalie	Koncentration	Temp.	Best�ndighet
1,4-Dioxan	100	20 �C	
2-Hydroxypropionic Acid	90	20 �C	
Acetic Acid	100	20 �C	
Aceton	100	20 �C	
Ammoniak	conc.	20 �C	
Ammonium Chloride	���	20 �C	
Amyl Alcohol	���	20 �C	
Apple Juice	���	20 �C	
Bensen	���	20 �C	
Bleaching Solution	12.5 cl	20 �C	
Boric Acid	100	20 �C	
Brake Fluid	���	20 �C	
Br�nsle (aromatfritt)	���	20 �C	
Butyl Acetate	���	20 �C	
Calcium Chloride	���	20 �C	
Carbon Disulfide	100	20 �C	
Carbon Tetrachloride	���	20 �C	
Citric Acid	10	20 �C	
Cyklohexanon	100	20 �C	
Cyklohexen	100	20 �C	
Diesel Fuel	���	20 �C	
Diethylene Oxide	���	20 �C	
Ethyl Acetate	100	20 �C	
Ethyl Alcohol	96	20 �C	
Ethylene Chloride	100	20 �C	
Fenol (vattenl.)	ca. 9	20 �C	
Food Oil	���	20 �C	

Kemikalie		Koncentration	Temp.	Beständighet
Formaldehyd (vattenl.)	40		20 Å°C	
Formic Acid	10		20 Å°C	
Frost Protection Agent	â€”		20 Å°C	
Glycerin	100		20 Å°C	
Glykol	100		20 Å°C	
Heating Oil	â€”		20 Å°C	
Heptan	100		20 Å°C	
Hydrochloric Acid	10		20 Å°C	
Hydrochloric Acid (concentrated)	conc.		20 Å°C	
Hydrofluoric Acid	40		20 Å°C	
Hydrogen Peroxide	10		20 Å°C	
Hydrogen Sulfide (aqueous)	â€”		20 Å°C	
Isopropyl Alcohol	100		20 Å°C	
Klor (gas)	100		20 Å°C	
Klorbensen	100		20 Å°C	
Kloroform	â€”		20 Å°C	
Kresol	â€”		20 Å°C	
Linseed Oil	â€”		20 Å°C	
Merkurokrom	â€”		20 Å°C	
Methyl Alcohol	100		20 Å°C	
Methyl Ethyl Ketone (MEK)	100		20 Å°C	
Methylene Chloride	100		20 Å°C	
Mineral Oils (aromatic free)	â€”		20 Å°C	
MjÅlk	â€”		20 Å°C	
Nitric Acid	10		20 Å°C	
Nitric Acid	50		20 Å°C	
Nitrobensen	â€”		20 Å°C	
Oxalic Acid	â€”		20 Å°C	
Ozone Gas	â‰¥0.5 ppm		20 Å°C	
Paraffine Oil	100		20 Å°C	
Perkloretylen	â€”		20 Å°C	
Petroleum	100		20 Å°C	
Petroleum Ether	100		20 Å°C	
Phosphoric Acid	50		20 Å°C	
Potassium Hydroxide liquor	50		20 Å°C	

