

Rundstång i PA6.6 GF30 75x1000 mm svart

Artikelnr P1002494

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densitet	1.3	g/cm ³	ISO 1183
Sträckgränspänning	100	MPa	ISO 527
Elasticitetsmodul (drag)	5900	MPa	ISO 527-2
Brottspänning	100	MPa	ISO 527-2
Brottåjning	5	%	ISO 527-2
Smältpunkt	257.5	°C	ISO 3146
Maximal drifttemperatur (korttid)	175	°C	UL746B
Maximal drifttemperatur	120	°C	
Minsta temperatur	-20	°C	
Värmeformvridning (HDT/A)	150	°C	ISO 75-2
Värmeformvridning (HDT/B)	250	°C	ISO 75
Dielektrisk styrka	30	kV/mm	IEC 60243-1
Volymresistivitet	~10 ¹¹ Ω·m	Ω·cm	IEC 60093
Dielektrisk konstant (1 MHz)	3.6	-	IEC 60250
Dielektrisk förlustfaktor (1 MHz)	0.0	-	IEC 60250
Termisk konduktivitet	0.31	W/(m·K)	DIN 52612
Ytresistivitet	~10 ¹¹ Ω	Ω	IEC 60093
Jämförande krypspänningsindex (CTI)	475	V	IEC 60112
Fuktabsorption till mättnad	3.6	%	ISO 62
Vattenabsorption till mättnad	5.5	%	ISO 62
Skårad slagseghet (Charpy)	6	kJ/m ²	ISO 179/1eA
Slagseghet (Charpy)	50	kJ/m ²	ISO 179/1eU
Termisk utvidningskoefficient	0.5	10 ⁻⁶ /K	ISO 11359
Hårdhet Shore D	85	° Shore D	ISO 868
Kultryckshårdhet	165	MPa	ISO 2039-1

2. Kemisk beständighet

● Beständigt
 ● Delvis beständigt
 ● Ej beständigt

Kemikalie	Konc.	Resultat
1,4-Dioxan	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Aceton	100	●
Ammoniak	conc.	●
Ammonium Chloride	â€”	●
Amyl Alcohol	â€”	●
Apple Juice	â€”	●
Bensen	â€”	●
Bleaching Solution	12.5 cl	●
Boric Acid	100	●
Brake Fluid	â€”	●
Bränsle (aromatfritt)	â€”	●
Butyl Acetate	â€”	●
Calcium Chloride	â€”	●
Carbon Disulfide	100	●
Carbon Tetrachloride	â€”	●
Citric Acid	10	●
Cyklohexanon	100	●
Cyklohexen	100	●
Diesel Fuel	â€”	●
Diethylene Oxide	â€”	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Fenol (vattenl.)	ca. 9	●
Food Oil	â€”	●
Formaldehyd (vattenl.)	40	●
Formic Acid	10	●
Frost Protection Agent	â€”	●
Glycerin	100	●
Glykol	100	●
Heating Oil	â€”	●
Heptan	100	●

Kemikalie	Konc.	Resultat
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	conc.	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	â€”	●
Isopropyl Alcohol	100	●
Klor (gas)	100	●
Klorbensen	100	●
Kloroform	â€”	●
Kresol	â€”	●
Linseed Oil	â€”	●
Merkurokrom	â€”	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Mineral Oils (aromatic free)	â€”	●
Mj�lk	â€”	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobensen	â€”	●
Oxalic Acid	â€”	●
Ozone Gas	â‰ƒ 0.5 ppm	●
Paraffine Oil	100	●
Perkloretylen	â€”	●
Petroleum	100	●
Petroleum Ether	100	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	â€”	●
Propyl Alcohol	â€”	●
Pyridin	â€”	●
Silicone Oil	â€”	●
Sodium Carbonate (aqueous)	â€”	●
Sodium Chloride (aqueous)	â€”	●

Kemikalie	Konc.	Resultat
Sodium Hydrogen Sulfit	â€”	●
Sodium Hydroxide liquor	60	●
Sodium Hydroxide liquor	15	●
Sodium Nitrate (aqueous)	â€”	●
Sodium Thiosulfate	â€”	●
Sulfuric Acid	96	●
Tetrahydrofuran (THF)	100	●
Toluen	100	●
Transformer Oil	â€”	●
Trikloretan	100	●
Vatten	â€”	●
Xylen	â€”	●
Ättika (standard)	5 - 10	●