



Rundst ng i PE Ultra HD 25x2000 mm m rkbl 

Artikelnr P1400256

1. Tekniskt datablad

Egenskap	V�rde	Enhet	Standard
Densitet	0.9	g/cm� ³	ISO 1183
Str�ckgr�nssp�nning	17	MPa	ISO 527
Elasticitetsmodul (drag)	691.7	MPa	ISO 527
Brott�njning	316.7	%	ISO 527
Sm�ltpunkt	135	��C	ISO 3146
Maximal drifttemperatur	10	��C	
Minsta temperatur	-200	��C	
Volymresistivitet	10� ¹¹ � ²	���	IEC 60093
Termisk konduktivitet	0.4	W/(m��K)	DIN 52612
Ytresistivitet	10� ¹¹ � ²	���	IEC 60093
Fuktabsorption till m��ttnad	0.01	%	
Vattenabsorption till m��ttnad	0.01	%	
Sk��rad slagseghet (Charpy)	80	kJ/m� ²	ISO 11542-2
Slagseghet (Charpy)	80	kJ/m� ²	ISO 11542-2
Termisk utvidgningskoefficient	1.7	10����/K	DIN 53 752
H��rdhet Shore D	60	�� Shore D	shore D
Kultrycksh��rdhet	35.6	MPa	ISO 2039-1

2. Kemisk best ndighet

  Best ndig   Delvis best ndig   Ej best ndig

Kemikalie	Konc.	Resultat
Calcium carbonate	���	�
Ethanol	10%	�
Iron oxide	���	�
Magnesium stearate	���	�
Olive oil	���	�

Kemikalie	Konc.	Resultat
Silicon dioxide	â€”	●
Titanium dioxide	â€”	●
Ä„ttiksyra	3%	●