



Rundst ng i PE Ultra HD Ast 180x2000 mm svart

Artikelnr P1400165

● Best ndig

● Delvis best ndig

● Ej best ndig

Kemikalie	Koncentration	Temp.	Best�ndighet
1,4-Dioxan	100%	20 �C	●
2-Hydroxypropionic Acid	90%	20 �C	●
Acetaldehyd	��	20 �C	●
Acetic Acid	100%	20 �C	●
Aceton	��	20 �C	●
Aceton	100%	20 �C	●
Acronal-dispersjoner	��	20 �C	●
Akrylonitril	��	20 �C	●
Allylacetat	��	20 �C	●
Allylalkohol	96%	20 �C	●
Allylklorid	��	20 �C	●
Aluminiumfluorid	Conc.	20 �C	●
Aluminiumhydroxid	��	20 �C	●
Aluminiumklorid, fast	��	20 �C	●
Aluminiumklorid, vattenl.	any	20 �C	●
Aluminiummetafosfat	��	20 �C	●
Aluminiumsulfat, fast	��	20 �C	●
Aluminiumsulfat, vattenl. m�ttad	��	20 �C	●
Ammoniak	concentrated	20 �C	●
Ammoniak, flytande	��	20 �C	●
Ammoniak, gas	��	20 �C	●
Ammonium Chloride	��	20 �C	●
Amyl Alcohol	��	20 �C	●
Anilin	any	20 �C	●
Anisol	��	20 �C	●
Apple Juice	��	20 �C	●
Bensen	technically grade	20 �C	●

Kemikalie	Koncentration	Temp.	BestÃndighet
Bensen	â€”	20 Â°C	●
Bensoesyra, vattenl.	any	20 Â°C	●
Bensylalkohol	â€”	20 Â°C	●
Benzaldehyd, vattenl.	any	20 Â°C	●
Bitumen	â€”	20 Â°C	●
Bleaching Solution	12.5 cl	20 Â°C	●
BlÃ¶ck	â€”	20 Â°C	●
Boric Acid	100%	20 Â°C	●
Brake Fluid	â€”	20 Â°C	●
Brom, flytande	100%	20 Â°C	●
BromvÃ¶tesyra, vattenl.	50%	20 Â°C	●
BrÃ¶nsl� (aromatfritt)	â€”	20 Â°C	●
Butanol, vattenl.	any	20 Â°C	●
Butyl Acetate	â€”	20 Â°C	●
Calcium Chloride	â€”	20 Â°C	●
Calcium carbonate	â€”	20 Â°C	●
Calcium carbonate	â€”	20 Â°C	●
Carbon Disulfide	100%	20 Â°C	●
Carbon Tetrachloride	â€”	20 Â°C	●
Caustic soda	any	20 Â°C	●
Cider	â€”	20 Â°C	●
Citric Acid	10%	20 Â°C	●
Citrusfruktjuicer	â€”	20 Â°C	●
Cyklohexan	â€”	20 Â°C	●
Cyklohexanol	â€”	20 Â°C	●
Cyklohexanon	100%	20 Â°C	●
Cyklohexanon	â€”	20 Â°C	●
Cyklohexen	100%	20 Â°C	●
Dibutyleter	â€”	20 Â°C	●
Dibutylftalat	â€”	20 Â°C	●
Diesel Fuel	â€”	20 Â°C	●
Diesel fuel	â€”	20 Â°C	●
Diethylene Oxide	â€”	20 Â°C	●
Diglykolsyra, vattenl.	30%	20 Â°C	●

[illegible]

Kemikalie	Koncentration	Temp.	Best�ndighet
Ftalsyra, vattenl.	50%	20 �C	●
Furfurol	��	20 �C	●
Garvsyra (tannin), vattenl.	10%	20 �C	●
Glycerin	100%	20 �C	●
Glycerin, aqueous	any	20 �C	●
Glykol	100%	20 �C	●
Glykol, aqueous	as supplied	20 �C	●
Glysantin	��	20 �C	●
Havsvatten	��	20 �C	●
Heating Oil	��	20 �C	●
Heptan	100%	20 �C	●
Heptan	��	20 �C	●
Hexan	��	20 �C	●
Honung	��	20 �C	●
Hydrochloric Acid	10%	20 �C	●
Hydrochloric Acid (concentrated)	concentrated	20 �C	●
Hydrofluoric Acid	40%	20 �C	●
Hydrogen Peroxide	10%	20 �C	●
Hydrogen Sulfide (aqueous solution)	��	20 �C	●
Isooktan	��	20 �C	●
Isopropanol	��	20 �C	●
Isopropyl Alcohol	100%	20 �C	●
Isopropyleter	��	20 �C	●
Jod i kaliumjodidl�sning	3% iodine	20 �C	●
J��rn(II)klorid, vattenl. m�ttad	��	20 �C	●
J��rn(II)sulfat, vattenl. m�ttad	��	20 �C	●
J��rn(III)klorid, vattenl.	any	20 �C	●
J��rn(III)klorid, vattenl. m�ttad	��	20 �C	●
J��rn(III)nitrat, vattenl. m�ttad	��	20 �C	●
J��rn(III)sulfat, vattenl. m�ttad	��	20 �C	●
Kalciumhypoklorit, vattenl. suspension	any	20 �C	●
Kamfer	��	20 �C	●
Klor (gas)	100%	20 �C	●
Klor, flytande	��	20 �C	●
Klorbensen	100%	20 �C	●

Kemikalie	Koncentration	Temp.	Beständighet
Klorbensen	â€”	20 Â°C	🟡
Kloroform	â€”	20 Â°C	🟡
Kloroform	technically grade	20 Â°C	🟡
KlorÄttiksyra, vattenl.	â‰ƒ85%	20 Â°C	🟢
Kokosolja	â€”	20 Â°C	🟢
Koldisulfid	â€”	20 Â°C	🔴
Kresol	100%	20 Â°C	🟢
Kresol	â€”	20 Â°C	🟢
Kromsyra-svavelsyra	â€”	20 Â°C	🔴
Kungsvatten	â€”	20 Â°C	🔴
Kvikksilver	â€”	20 Â°C	🟢
Linolja	technically grade	20 Â°C	🟢
Linseed Oil	â€”	20 Â°C	🟢
Litiumbromid	â€”	20 Â°C	🟢
Magnesium stearate	â€”	20 Â°C	🟢
Magnesium stearate	â€”	20 Â°C	🟢
Maleinsyra, vattenl.	any	20 Â°C	🟢
Melass	â€”	20 Â°C	🟢
Mentol	â€”	20 Â°C	🟢
Merkurokrom	â€”	20 Â°C	🟢
Metanol	technically grade	20 Â°C	🟢
Methyl Alcohol	100%	20 Â°C	🟢
Methyl Ethyl Ketone (MEK)	100%	20 Â°C	🔴
Methyl ethyl ketone	technically grade	20 Â°C	🟢
Methylene Chloride	100%	20 Â°C	🟡
Metylklorid	gaseous, technically grade	20 Â°C	🔴
Mineral Oil (aromatic free)	â€”	20 Â°C	🟢
MjÄlk	â€”	20 Â°C	🟢
MjÄlk	â€”	20 Â°C	🟢
Motor oil (heavy duty oil) without additives	â€”	20 Â°C	🟢
Myrsyra, vattenl.	85%	20 Â°C	🟢
Nafta	â€”	20 Â°C	🟢
Naftalen	â€”	20 Â°C	🟢
Natriumbromid	â€”	20 Â°C	🟢

Kemikalie	Koncentration	Temp.	Best�ndighet
Natriumhydroxid, fast	���	20 ��C	�
Natriumhydroxid, vattenl.	any	20 ��C	�
Nitric Acid	10%	20 ��C	�
Nitric Acid (50%)	50%	20 ��C	�
Nitrobensen	���	20 ��C	�
Nitrobensen	���	20 ��C	�
Oils, ethereal	���	20 ��C	�
Oleum	any	20 ��C	�
Olive oil	���	100 ��C	�
Olive oil	���	100 ��C	�
Olive oil	���	100 ��C	�
Olive oil	���	20 ��C	�
Oljesyra	���	20 ��C	�
Oljor, vegetabiliska och animaliska	���	20 ��C	�
Oxalic Acid	���	20 ��C	�
Oxalsyra, vattenl.	any	20 ��C	�
Ozon	50 ppm	20 ��C	�
Ozone Gas	���0.5 ppm	20 ��C	�
Paraffine Oil	100%	20 ��C	�
Perkloretylen	���	20 ��C	�
Perklorsyra, vattenl.	50%	20 ��C	�
Perklorsyra, vattenl.	70%	20 ��C	�
Perklorsyra, vattenl.	20%	20 ��C	�
Petroleum	���	20 ��C	�
Petroleum	100%	20 ��C	�
Petroleum Ether	100%	20 ��C	�
Petroleumeter	���	20 ��C	�
Phosphoric Acid	50%	20 ��C	�
Photographic developers	���	20 ��C	�
Photographic emulsions	as supplied	20 ��C	�
Photographic fixing baths	as supplied	20 ��C	�
Polyesterhartser	���	20 ��C	�
Potassium Hydroxide liquor	50%	20 ��C	�
Premium Fuel	���	20 ��C	�

Kemikalie	Koncentration	Temp.	Best�ndighet
Propionsyra, vattenl.	any	20 �C	●
Propyl Alcohol	���	20 �C	●
Pyridin	���	20 �C	●
Pyridin	���	20 �C	●
Salpetersyra, vattenl.	25%	20 �C	●
Salpetersyra, vattenl.	50%	20 �C	●
Saltsyra, vattenl.	any	20 �C	●
Silicon dioxide	���	20 �C	●
Silicon dioxide	���	20 �C	●
Silicone Oil	���	20 �C	●
Silikonolja	technically grade	20 �C	●
Sm�r	���	20 �C	●
Sockersirap	���	20 �C	●
Sodium Carbonate (aqueous)	���	20 �C	●
Sodium Chloride (aqueous)	���	20 �C	●
Sodium Hydrogen Sulfite	���	20 �C	●
Sodium Hydroxide liquor	15%	20 �C	●
Sodium Hydroxide liquor (60%)	60%	20 �C	●
Sodium Nitrate (aqueous)	���	20 �C	●
Sodium Thiosulfate	���	20 �C	●
Sodium borate	���	20 �C	●
Stearinsyra	���	20 �C	●
Sulfuric Acid	96%	20 �C	●
Svavelsyra, vattenl.	80%	20 �C	●
Svavelsyra, vattenl.	70%	20 �C	●
Svavelsyra, vattenl.	���50%	20 �C	●
Svavelsyra, vattenl.	98%	20 �C	●
Sylt	���	20 �C	●
Syre	���	20 �C	●
Talg	technically grade	20 �C	●
Tenn(II)klorid, vattenl.	any	20 �C	●
Tenn(IV)klorid, vattenl.	saturated	20 �C	●
Terpentinolja	technically grade	20 �C	●
Tetrahydrofuran	technically grade	20 �C	●
Tetrahydrofuran (THF)	100%	20 �C	●

