



PLASTSHOP.SE

PlastShop.se  
Söderleden 22  
587 31 Linköping  
Sverige



PLASTSHOP.SE

## Kemisk beständighet

PlastShop.se • 2026-02-27

# PEEK GF30 36x3000 mm beige

Artikelnummer: P1500926

## Kemisk beständighet

**A** Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

| KEMIKALIE               | BETYG | KONCENTRATION | TEMPERATUR |
|-------------------------|-------|---------------|------------|
| 1,4-Dioxane             | A     | 100%          |            |
| 2-Hydroxypropionic Acid | A     | 90%           |            |
| Acetic Acid             | A     | 100%          |            |
| Acetone                 | A     | 100%          |            |
| Ammonia                 | A     |               |            |
| Ammonium Chloride       | A     |               |            |
| Amyl Alcohol            | A     |               |            |
| Apple Juice             | A     |               |            |
| Benzene                 | A     |               |            |
| Boric Acid              | A     | 100%          |            |
| Brake Fluid             | A     |               |            |
| Butyl Acetate           | A     |               |            |
| Calcium Chloride        | A     |               |            |
| Carbon Tetrachloride    | A     |               |            |
| Chlorine (gas)          | A     | 100%          |            |
| Chlorobenzene           | A     | 100%          |            |
| Chloroform              | A     |               |            |
| Citric Acid             | A     | 10%           |            |
| Cyclohexanone           | A     | 100%          |            |
| Cyclohexene             | A     | 100%          |            |



PLASTSHOP.SE

PlastShop.se  
Söderleden 22  
587 31 Linköping  
Sverige

| KEMIKALIE                        | BETYG | KONCENTRATION | TEMPERATUR |
|----------------------------------|-------|---------------|------------|
| Diesel Fuel                      | A     |               |            |
| Diethylene Oxide                 | A     |               |            |
| Ethyl Acetate                    | A     | 100%          |            |
| Ethyl Alcohol                    | A     | 96%           |            |
| Ethylene Chloride                | A     | 100%          |            |
| Food Oil                         | A     |               |            |
| Formaldehyde (aqueous)           | A     | 40%           |            |
| Formic Acid                      | B     | 10%           |            |
| Frost Protection Agent           | A     |               |            |
| Fuel, aromatic free              | A     |               |            |
| Glycerin                         | A     | 100%          |            |
| Glycol                           | A     | 100%          |            |
| Heating Oil                      | A     |               |            |
| Heptane                          | A     | 100%          |            |
| Hydrochloric Acid                | A     | 10%           |            |
| Hydrochloric Acid (concentrated) | B     |               |            |
| Hydrofluoric Acid                | D     | 40%           |            |
| Hydrogen Peroxide                | A     | 10%           |            |
| Hydrogen Sulfide (aqueous)       | A     |               |            |
| Isopropyl Alcohol                | A     | 100%          |            |
| Linseed Oil                      | A     |               |            |
| Mercurochrome                    | B     |               |            |
| Methyl Alcohol                   | A     | 100%          |            |
| Methyl Ethyl Ketone (MEK)        | A     | 100%          |            |
| Methylene Chloride               | A     | 100%          |            |
| Milk                             | A     |               |            |
| Mineral Oils (aromatic free)     | A     |               |            |
| Nitric Acid                      | A     | 10%           |            |
| Nitric Acid                      | A     | 50%           |            |



PLASTSHOP.SE

PlastShop.se  
Söderleden 22  
587 31 Linköping  
Sverige

| KEMIKALIE                  | BETYG | KONCENTRATION | TEMPERATUR |
|----------------------------|-------|---------------|------------|
| Nitrobenzene               | A     |               |            |
| Oxalic Acid                | A     |               |            |
| Ozone Gas                  | A     |               |            |
| Paraffine Oil              | A     | 100%          |            |
| Perchloroethylene          | A     |               |            |
| Petroleum                  | A     | 100%          |            |
| Petroleum Ether            | A     | 100%          |            |
| Phenol (aqueous)           | A     | 9%            |            |
| Phosphoric Acid            | A     | 50%           |            |
| Potassium Hydroxide liquor | A     | 50%           |            |
| Premium Fuel               | A     |               |            |
| Propyl Alcohol             | A     |               |            |
| Pyridine                   | A     |               |            |
| Silicone Oil               | A     |               |            |
| Sodium Carbonate (aqueous) | A     |               |            |
| Sodium Chloride (aqueous)  | A     |               |            |
| Sodium Hydrogen Sulfite    | A     |               |            |
| Sodium Hydroxide liquor    | A     | 15%           |            |
| Sodium Hydroxide liquor    | A     | 60%           |            |
| Sodium Nitrate (aqueous)   | A     |               |            |
| Sodium Thiosulfate         | A     |               |            |
| Sulfuric Acid              | D     | 96%           |            |
| Tetrahydrofuran (THF)      | A     | 100%          |            |
| Toluene                    | A     | 100%          |            |
| Transformer Oil            | A     |               |            |
| Trichloroethylene          | A     | 100%          |            |
| Vinegar (standard)         | A     | 5-10%         |            |
| Water                      | A     |               |            |
| Xylene                     | A     |               |            |



PLASTSHOP.SE

PlastShop.se  
Söderleden 22  
587 31 Linköping  
Sverige

---

PlastShop.se  
Söderleden 22, Linköping, Sverige

Tel: +46 13 328 94 00  
info@plastshop.se  
<https://plastshop.se>

Informationen i detta dokument baseras på aktuell kunskap och erfarenhet. Värden kan variera beroende på bearbetning och användningsförhållanden. Alla uppgifter utan garanti.