

PEEK HT 56x3000 mm svart

Artikelnummer: P1500993

Kemisk beständighet

A Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
1,4-Dioxan	resistant	100%	
2-Hydroxipropionsyra (mjölksyra)	resistant	90%	
Aceton	resistant	100%	
Ammoniak	resistant		
Ammoniumklorid	resistant		
Amylalkohol	resistant		
Bensen	resistant		
Bensin (premium)	resistant		
Borsyra	resistant	100%	
Bromsvätska	resistant		
Bränsle, aromatfritt	resistant		
Butylacetat	resistant		
Citronsyra	resistant	10%	
Cyklohexanon	resistant	100%	
Cyklohexen	resistant	100%	
Diesel	resistant		
Dietylenoxid	resistant		
Eldningsolja	resistant		
Etylacetat	resistant	100%	
Etylalkohol (etanol)	resistant	96%	
Etylenklorid	resistant	100%	
Fenol (vattenl.)	resistant	9%	

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
Fluorvätesyra	not_resistant	40%	
Formaldehyd (vattenl.)	resistant	40%	
Fosforsyra	resistant	50%	
Frostskyddsmedel	resistant		
Glycerin	resistant	100%	
Glykol	resistant	100%	
Heptan	resistant	100%	
Isopropylalkohol	resistant	100%	
Kalciumklorid	resistant		
Kaliumhydroxidlösning	resistant	50%	
Klor (gas)	resistant	100%	
Klorbensen	resistant	100%	
Kloroform	resistant		
Koltetraklorid	resistant		
Linolja	resistant		
Matolja	resistant		
Merkurokrom	partially_resistant		
Metylalkohol (metanol)	resistant	100%	
Metylenklorid	resistant	100%	
Metyletylketon (MEK)	resistant	100%	
Mineraloljor (aromatfria)	resistant		
Mjök	resistant		
Myrsyra	partially_resistant	10%	
Natriumhydroxidlösning (natronlut)	resistant	60%	
Natriumhydroxidlösning (natronlut)	resistant	15%	
Natriumkarbonat (vattenl.)	resistant		
Natriumklorid (vattenl.)	resistant		
Natriumnitrat (vattenl.)	resistant		
Natriumtiosulfat	resistant		
Natriumvätesulfit	resistant		
Nitrobensen	resistant		

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
Oxalsyra	resistant		
Ozon (gas)	resistant		
Paraffinolja	resistant	100%	
Perkloretylen	resistant		
Petroleum	resistant	100%	
Petroleometer	resistant	100%	
Propylalkohol	resistant		
Pyridin	resistant		
Salpetersyra	resistant	10%	
Salpetersyra	resistant	50%	
Saltsyra	resistant	10%	
Saltsyra (konc.)	partially_resistant		
Silikonolja	resistant		
Svavelsyra	not_resistant	96%	
Tetrahydrofuran (THF)	resistant	100%	
Toluen	resistant	100%	
Transformatorolja	resistant		
Trikloreten	resistant	100%	
Vatten	resistant		
Väteperoxid	resistant	10%	
Vätesulfid (vattenl.)	resistant		
Xylen	resistant		
Äppeljuice	resistant		
Ättika (standard)	resistant	5-10%	
Ättiksyra	resistant	100%	