

PEEK+PTFE 65x3000 mm beige

Artikelnr P1501501

● Beständigt ● Delvis beständigt ● Ej beständigt

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxan	100	20 Å°C	●
2-Hydroxypropionic Acid	90	20 Å°C	●
Acetic Acid	100	20 Å°C	●
Aceton	100	20 Å°C	●
Ammoniak	â€”	20 Å°C	●
Ammonium Chloride	â€”	20 Å°C	●
Amyl Alcohol	â€”	20 Å°C	●
Apple Juice	â€”	20 Å°C	●
Bensen	â€”	20 Å°C	●
Bleaching Solution	â€”	20 Å°C	●
Boric Acid	100	20 Å°C	●
Brake Fluid	â€”	20 Å°C	●
Br��nsle, aromatfritt	â€”	20 Å°C	●
Butyl Acetate	â€”	20 Å°C	●
Calcium Chloride	â€”	20 Å°C	●
Carbon Disulfide	100	20 Å°C	●
Carbon Tetrachloride	â€”	20 Å°C	●
Citric Acid	10	20 Å°C	●
Cyklohexanon	100	20 Å°C	●
Cyklohexen	100	20 Å°C	●
Diesel Fuel	â€”	20 Å°C	●
Diethylene Oxide	â€”	20 Å°C	●
Ethyl Acetate	100	20 Å°C	●
Ethyl Alcohol	96	20 Å°C	●
Ethylene Chloride	100	20 Å°C	●
Fenol (vattenl.)	9	20 Å°C	●
Food Oil	â€”	20 Å°C	●

Kemikalie		Koncentration	Temp.	Best�ndighet
Formaldehyd (vattenl.)	40		20 ��C	�
Formic Acid	10		20 ��C	�
Frost Protection Agent	���		20 ��C	�
Glycerin	100		20 ��C	�
Glykol	100		20 ��C	�
Heating Oil	���		20 ��C	�
Heptan	100		20 ��C	�
Hydrochloric Acid	10		20 ��C	�
Hydrochloric Acid (concentrated)	���		20 ��C	�
Hydrofluoric Acid	40		20 ��C	�
Hydrogen Peroxide	10		20 ��C	�
Hydrogen Sulfide (aqueous)	���		20 ��C	�
Isopropyl Alcohol	100		20 ��C	�
Klor (gas)	100		20 ��C	�
Klorbensen	100		20 ��C	�
Kloroform	���		20 ��C	�
Kresol	���		20 ��C	�
Linseed Oil	���		20 ��C	�
Merkurokrom	���		20 ��C	�
Methyl Alcohol	100		20 ��C	�
Methyl Ethyl Ketone (MEK)	100		20 ��C	�
Methylene Chloride	100		20 ��C	�
Mineral Oils (aromatic free)	���		20 ��C	�
Mj��lk	���		20 ��C	�
Nitric Acid	10		20 ��C	�
Nitric Acid	50		20 ��C	�
Nitrobensen	���		20 ��C	�
Oxalic Acid	���		20 ��C	�
Ozone Gas	���		20 ��C	�
Paraffine Oil	100		20 ��C	�
Perkloretylen	���		20 ��C	�
Petroleum	100		20 ��C	�
Petroleum Ether	100		20 ��C	�
Phosphoric Acid	50		20 ��C	�
Potassium Hydroxide liquor	50		20 ��C	�

