



PLASTSHOP.SE

PlastShop.se
Söderleden 22
587 31 Linköping
Sverige



PLASTSHOP.SE

Kemisk beständighet

PlastShop.se • 2026-02-27

PET FG 140x1000 mm natur

Artikelnummer: P1003932

Kemisk beständighet

A Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

| KEMIKALIE | BETYG | KONCENTRATION | TEMPERATUR |
|--------------------|-------|---------------|------------|
| 1,4-Dioxane | B | 100% | |
| 1,4-Dioxane | B | 100% | 60 °C |
| Acetic Acid | A | 100% | |
| Acetic Acid | D | 100% | |
| Acetic Acid | D | 100% | 60 °C |
| Acetone | B | 100% | |
| Acetone | D | 100% | 60 °C |
| Ammonia | B | conc.% | |
| Ammonia | D | conc.% | 60 °C |
| Apple Juice | A | | |
| Apple Juice | A | | |
| Benzene | B | | |
| Benzene | D | | 60 °C |
| Bleaching Solution | A | | |
| Brake Fluid | A | | 60 °C |
| Brake Fluid | A | | |
| Butyl Acetate | A | | 60 °C |
| Butyl Acetate | A | | |
| Calcium Chloride | A | | |
| Calcium Chloride | A | | 60 °C |
| Carbon Disulfide | B | 100% | 60 °C |



PLASTSHOP.SE

PlastShop.se
Söderleden 22
587 31 Linköping
Sverige

| KEMIKALIE | BETYG | KONCENTRATION | TEMPERATUR |
|------------------------|-------|---------------|------------|
| Carbon Disulfide | A | 100% | |
| Carbon Tetrachloride | B | | 60 °C |
| Carbon Tetrachloride | A | | |
| Carbon Tetrachloride | A | | |
| Chlorobenzene | D | 100% | 60 °C |
| Chlorobenzene | A | 100% | |
| Chlorobenzene | D | 100% | |
| Chloroform | D | | 60 °C |
| Chloroform | D | | |
| Citric Acid | A | 10% | |
| Citric Acid | B | 10% | 60 °C |
| Diesel Fuel | A | | 60 °C |
| Diesel Fuel | A | | |
| Diethylene Oxide | A | | |
| Diethylene Oxide | A | | |
| Ethyl Acetate | A | 100% | |
| Ethyl Acetate | D | 100% | 60 °C |
| Ethyl Alcohol | A | 96% | |
| Ethyl Alcohol | A | 96% | |
| Ethyl Alcohol | A | 96% | 60 °C |
| Ethylene Chloride | B | 100% | |
| Ethylene Chloride | D | 100% | 60 °C |
| Food Oil | A | | |
| Food Oil | A | | |
| Food Oil | A | | 60 °C |
| Formic Acid | B | 10% | 60 °C |
| Formic Acid | A | 10% | |
| Frost Protection Agent | A | | |



PLASTSHOP.SE

PlastShop.se
Söderleden 22
587 31 Linköping
Sverige

| KEMIKALIE | BETYG | KONCENTRATION | TEMPERATUR |
|------------------------------------|-------|---------------|------------|
| Frost Protection Agent | B | | 60 °C |
| Fuel aromatic free | A | | 60 °C |
| Fuel aromatic free | A | | |
| Glycerin | A | 100%% | |
| Glycerin | A | 100% | 60 °C |
| Glycerin | A | 100% | |
| Glycol | B | 100% | 60 °C |
| Glycol | A | 100% | |
| Heating Oil | A | | |
| Heating Oil | A | | 60 °C |
| Heptane | A | 100% | 60 °C |
| Heptane | A | 100% | |
| Hydrochloric Acid | D | conc.% | 60 °C |
| Hydrochloric Acid | A | 10% | |
| Hydrochloric Acid | B | 10% | 60 °C |
| Hydrochloric Acid | D | conc.% | |
| Hydrochloric Acid (concentrated) | A | conc.% | |
| Hydrofluoric Acid | D | 40% | |
| Hydrofluoric Acid | D | 40% | 60 °C |
| Hydrofluoric Acid | A | 40%% | |
| Hydrogen Peroxide | B | 10% | 60 °C |
| Hydrogen Peroxide | A | 10% | |
| Hydrogen Sulfide, aqueous solution | A | | |
| Isopropyl Alcohol | B | 100% | 60 °C |
| Isopropyl Alcohol | A | 100%% | |
| Isopropyl Alcohol | A | 100% | |
| Linseed Oil | A | | |
| Linseed Oil | A | | 60 °C |
| Mercurochrome | A | | |



PLASTSHOP.SE

PlastShop.se
Söderleden 22
587 31 Linköping
Sverige

| KEMIKALIE | BETYG | KONCENTRATION | TEMPERATUR |
|----------------------------|-------|---------------|------------|
| Methyl Alcohol | A | 100% | |
| Methyl Alcohol | A | 100% | |
| Methyl Alcohol | B | 100% | 60 °C |
| Methyl Ethyl Ketone (MEK) | B | 100% | 60 °C |
| Methyl Ethyl Ketone (MEK) | A | 100% | |
| Methylene Chloride | D | 100% | 60 °C |
| Methylene Chloride | D | 100% | |
| Milk | A | | 60 °C |
| Milk | A | | |
| Mineral Oils aromatic free | A | | 60 °C |
| Mineral Oils aromatic free | A | | |
| Nitric Acid | B | 10% | 60 °C |
| Nitric Acid | A | 10% | |
| Nitric Acid | A | 10% | |
| Nitric Acid | D | 50% | |
| Nitric Acid | D | 50% | 60 °C |
| Paraffine Oil | A | 100% | 60 °C |
| Paraffine Oil | A | 100% | |
| Perchloroethylene | D | | 60 °C |
| Perchloroethylene | A | | |
| Petroleum | A | 100% | |
| Petroleum | A | 100% | |
| Petroleum Ether | A | 100% | 60 °C |
| Petroleum Ether | A | 100% | |
| Petroleum Ether | A | 100% | |
| Phenol aqueous | D | ca.9% | |
| Phosphoric Acid | A | 50% | |
| Phosphoric Acid | B | 50% | 60 °C |
| Potassium Hydroxide liquor | D | 50% | 60 °C |



PLASTSHOP.SE

PlastShop.se
Söderleden 22
587 31 Linköping
Sverige

| KEMIKALIE | BETYG | KONCENTRATION | TEMPERATUR |
|----------------------------|-------|---------------|------------|
| Potassium Hydroxide liquor | D | 50% | |
| Premium Fuel | B | | 60 °C |
| Premium Fuel | A | | |
| Propyl Alcohol | A | | |
| Propyl Alcohol | D | | 60 °C |
| Silicone Oil | A | | 60 °C |
| Silicone Oil | A | | |
| Sodium Carbonate aqueous | A | | 60 °C |
| Sodium Carbonate aqueous | A | | |
| Sodium Chloride aqueous | A | | 60 °C |
| Sodium Chloride aqueous | A | | |
| Sodium Hydrogen Sulfite | A | | 60 °C |
| Sodium Hydrogen Sulfite | A | | |
| Sodium Hydrogen Sulfite | B | | |
| Sodium Hydroxide liquor | D | 60% | 60 °C |
| Sodium Hydroxide liquor | D | 15% | 60 °C |
| Sodium Hydroxide liquor | D | 60% | |
| Sodium Hydroxide liquor | D | 15% | |
| Sodium Nitrate aqueous | A | | |
| Sodium Thiosulfate | A | | |
| Sulfuric Acid | D | 96% | 60 °C |
| Sulfuric Acid | D | 96% | |
| Tetrahydrofuran THF | D | 100% | |
| Tetrahydrofuran THF | D | 100% | 60 °C |
| Toluene | D | 100% | 60 °C |
| Toluene | A | 100% | |
| Toluene | A | 100% | |
| Transformer Oil | A | | |
| Transformer Oil | A | | 60 °C |



PLASTSHOP.SE

PlastShop.se
Söderleden 22
587 31 Linköping
Sverige

| KEMIKALIE | BETYG | KONCENTRATION | TEMPERATUR |
|-------------------|-------|---------------|------------|
| Trichloroethylene | B | 100% | |
| Trichloroethylene | D | 100% | 60 °C |
| Vinegar standard | B | 5-10% | 60 °C |
| Vinegar standard | A | 5-10% | |
| Vinegar, standard | A | 5-10%% | |
| Water | A | | |
| Water | D | | 60 °C |
| Xylene | D | | 60 °C |
| Xylene | B | | |

PlastShop.se
Söderleden 22, Linköping, Sverige

Tel: +46 13 328 94 00
info@plastshop.se
<https://plastshop.se>

Informationen i detta dokument baseras på aktuell kunskap och erfarenhet. Värden kan variera beroende på bearbetning och användningsförhållanden. Alla uppgifter utan garanti.