



Rundstång i POM H 32x1000 mm natur

Artikelnr P1008622

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densitet	3	g/cm³	DIN EN ISO 1183-1
Sträckgränsspänning	53	MPa	DIN EN ISO 527-2
Elasticitetsmodul (drag)	3000	MPa	DIN EN ISO 527-2
Brottåjning	8	%	DIN EN ISO 527-2
Smältpunkt	179	°C	DIN EN ISO 11357
Maximal drifttemperatur (korttid)	150	°C	
Maximal drifttemperatur	110	°C	
Värmeutvidgning (HDT/A)	141	°C	
Vicat mjukningstemperatur (VST/B/50)	90	°C	DIN EN ISO 306
Dielektrisk styrka	23	kV/mm	ISO 60243-1
Volymresistivitet	10¹¹	Î©	DIN EN 62631-3-1
Dielektrisk konstant (1 MHz)	2.4	-	IEC 60250
Brandklassning (UL 94)	60695		UL 94
Bärkraft	53	MPa	DIN EN ISO 527-2
Termisk konduktivitet	0.46	W/(m·K)	ISO 22007-4
Ytresistivitet	10¹¹	Î©	DIN EN 62631-3-2
Fuktabsorption till mättnad	0.1	%	DIN EN ISO 62
Skärslagseghet (Charpy)	25	kJ/m²	DIN EN ISO 179-1
Slagseghet (Charpy)	2	kJ/m²	DIN EN ISO 179-1
Termisk utvidgningskoefficient	23	10⁻⁵ /K	DIN EN ISO 11359-1
Hårdhet Shore D	81	° Shore D	DIN EN ISO 868

2. Kemisk beständighet

Beständig Delvis beständig Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxan	100%	

Kemikalie	Konc.	Resultat
2-Hydroxypropionic Acid	90%	
Acetic Acid	100%	
Aceton	100%	
Ammoniak	conc.	
Ammonium Chloride	â€”	
Amyl Alcohol	â€”	
Apple Juice	â€”	
Bensen	â€”	
Bleaching Solution	12.5 cl	
Boric Acid	100%	
Brake Fluid	â€”	
Br��nsle, aromatfritt	â€”	
Butyl Acetate	â€”	
Calcium Chloride	â€”	
Carbon Disulfide	100%	
Carbon Tetrachloride	â€”	
Citric Acid	10%	
Cyklohexanon	100%	
Cyklohexen	100%	
Diesel Fuel	â€”	
Diethylene Oxide	â€”	
Ethyl Acetate	100%	
Ethyl Alcohol	96%	
Ethylene Chloride	100%	
Fenol, vattenl.	ca. 9%	
Food Oil	â€”	
Formaldehyd, vattenl.	40%	
Formic Acid	10%	
Frost Protection Agent	â€”	
Glycerin	100%	
Glykol	100%	
Heating Oil	â€”	
Heptan	100%	
Hydrochloric Acid	10%	
Hydrochloric Acid (concentrated)	conc.	

Kemikalie	Konc.	Resultat
Hydrofluoric Acid	40%	
Hydrogen Peroxide	10%	
Hydrogen Sulfide, aqueous solution	â€”	
Isopropyl Alcohol	100%	
Klor (gas)	100%	
Klorbensen	100%	
Kloroform	â€”	
Kresol	â€”	
Linseed Oil	â€”	
Merkurokrom	â€”	
Methyl Alcohol	100%	
Methyl Ethyl Ketone (MEK)	100%	
Methylene Chloride	100%	
Mineral Oils (aromatic free)	â€”	
Mj�lk	â€”	
Nitric Acid	10%	
Nitric Acid (50%)	50%	
Nitrobensen	â€”	
Oxalic Acid	â€”	
Ozone Gas	â‰‰0.5 ppm	
Paraffine Oil	100%	
Perkloretylen	â€”	
Petroleum	100%	
Petroleum Ether	100%	
Phosphoric Acid	50%	
Potassium Hydroxide liquor	50%	
Premium Fuel	â€”	
Propyl Alcohol	â€”	
Pyridin	â€”	
Silicone Oil	â€”	
Sodium Carbonate, aqueous	â€”	
Sodium Chloride, aqueous	â€”	
Sodium Hydrogen Sulfite	â€”	

Kemikalie	Konc.	Resultat
Sodium Hydroxide liquor (15%)	15%	
Sodium Hydroxide liquor (60%)	60%	
Sodium Nitrate, aqueous	â€”	
Sodium Thiosulfate	â€”	
Sulfuric Acid	96%	
Tetrahydrofuran, THF	100%	
Toluen	100%	
Transformer Oil	â€”	
Trikloreten	100%	
Vatten	â€”	
Xylen	â€”	
Ättika, standard	5-10%	