

Egenskap	Värde	Enhet	Standard
Hårddhet Shore D	72	Å° Shore D	ISO 868
Kultryckshårddhet	110	MPa	ISO 2039

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxan	100	●
2-Hydroxipropionsyra (mjölksyra)	90	●
Aceton	100	●
Ammoniak	â€”	●
Ammoniumklorid	â€”	●
Amylalkohol	â€”	●
Bensen	â€”	●
Bensin (premium)	â€”	●
Blekningslösning	â€”	●
Borsyra	100	●
Bromsvätska	â€”	●
Bromsle, aromatfritt	â€”	●
Butylacetat	â€”	●
Citronsyra	10	●
Cyklohexanon	100	●
Cyklohexen	100	●
Diesel	â€”	●
Dietylenoxid	â€”	●
Eldningsolja	â€”	●
Etylacetat	100	●
Etylalkohol (etanol)	96	●
Etylenklorid	100	●
Fenol, vattenl.	ca. 9	●
Fluorvätsyra	40	●
Formaldehyd, vattenl.	40	●
Fosforsyra	50	●
Frostskyddsmedel	â€”	●

Kemikalie	Konc.	Resultat
Glycerin	100	●
Glykol	100	●
Heptan	100	●
Isopropylalkohol	100	●
Kalciumklorid	â€”	●
Kaliumhydroxidl��sning	50	●
Klor (gas)	100	●
Klorbensen	100	●
Kloroform	â€”	●
Koldisulfid	100	●
Koltetraklorid	â€”	●
Kresol	â€”	●
Linolja	â€”	●
Matolja	â€”	●
Merkurokrom	â€”	●
Metylalkohol (metanol)	100	●
Metylenklorid	100	●
Metyletylketon (MEK)	100	●
Mineraloljor (aromatfria)	â€”	●
Mj��lk	â€”	●
Myrsyra	10	●
Natriumhydroxidl��sning (natronlut)	60	●
Natriumhydroxidl��sning (natronlut)	15	●
Natriumkarbonat, vattenl.	â€”	●
Natriumklorid, vattenl.	â€”	●
Natriumnitrat, vattenl.	â€”	●
Natriumtiosulfat	â€”	●
Natriumv��tesulfit	â€”	●
Nitrobensen	â€”	●
Oxalsyra	â€”	●
Ozon (gas)	��� 0.5 ppm	●
Paraffinolja	100	●
Perkloretylen	â€”	●
Petroleumeter	100	●

Kemikalie	Konc.	Resultat
Propylalkohol	â€”	●
Pyridin	â€”	●
Salpetersyra	10	●
Salpetersyra	50	●
Saltsyra	10	●
Saltsyra (konc.)	â€”	●
Silikonolja	â€”	●
Svavelsyra	96	●
Tetrahydrofuran (THF)	100	●
Toluen	100	●
Transformatorolja	â€”	●
Trikloretan	100	●
Vatten	â€”	●
Vätteperoxid	10	●
Vättesulfid, vattenl.	â€”	●
Xylen	â€”	●
Ättika, standard	5 - 10	●
Ättiksyra	100	●