



Rundst ng i PPS 20x1000 mm svart

Artikelnr P1010400

Best ndig

Delvis best ndig

Ej best ndig

Kemikalie	Koncentration	Temp.	Best�ndighet
1,4-Dioxan	100	20 �C	
Aceton	100	20 �C	
Ammoniak	��	20 �C	
Ammoniumklorid	��	20 �C	
Bensen	��	20 �C	
Bensin (premium)	��	20 �C	
Bromsv��tska	��	20 �C	
Br��nsle, aromatfritt	��	20 �C	
Butylacetat	��	20 �C	
Diesel	��	20 �C	
Dietylenoxid	��	20 �C	
Etylacetat	100	20 �C	
Etylalkohol (etanol)	96	20 �C	
Fenol, vattenl.	9	20 �C	
Fosforsyra	50	20 �C	
Frostskyddsmedel	��	20 �C	
Glycerin	100	20 �C	
Isopropylalkohol	100	20 �C	
Kalciumklorid	��	20 �C	
Klorbensen	100	20 �C	
Kloroform	��	20 �C	
Koltetraklorid	��	20 �C	
Metylalkohol (metanol)	100	20 �C	
Metylenklorid	100	20 �C	
Metyletylketon (MEK)	100	20 �C	
Mineraloljor (aromatfria)	��	20 �C	
Natriumklorid, vattenl.	��	20 �C	

Kemikalie	Koncentration	Temp.	Beständighet
Natronlut (15%)	15	20 Å°C	
Natronlut (60%)	60	20 Å°C	
Perkloretylen	â€”	20 Å°C	
Salpetersyra (10%)	10	20 Å°C	
Salpetersyra (50%)	50	20 Å°C	
Saltsyra (10%)	10	20 Å°C	
Saltsyra (konc.)	â€”	20 Å°C	
Svavelsyra	96	20 Å°C	
Tetrahydrofuran (THF)	100	20 Å°C	
Toluen	100	20 Å°C	
Transformatorolja	â€”	20 Å°C	
Trikloreten	100	20 Å°C	
Vatten	â€”	20 Å°C	
Xylen	â€”	20 Å°C	