

PVC U 5"x1525 mm mörkgrå

Artikelnummer: P2202076

Kemisk beständighet

A Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
1,4-Dioxane	D	100%%	
2-Hydroxypropionic Acid	A	90%%	
Acetic Acid	A	100%%	
Acetone	D	100%%	
Ammonia	A	conc.%	
Ammonium Chloride	A		
Amyl Alcohol	A		
Apple Juice	A		
Benzene	D		
Bleaching Solution	A	12.5 cl%	
Boric Acid	A	100%%	
Brake Fluid	A		
Butyl Acetate	D		
Calcium Chloride	A		
Carbon Disulfide	D	100%%	
Carbon Tetrachloride	D		
Chlorine (gas)	B	100%%	
Chlorobenzene	D	100%%	
Chloroform	D		
Citric Acid	A	10%%	

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
Cresol	D		
Cyclohexanone	D	100%%	
Cyclohexene	A	100%%	
Diesel Fuel	A		
Diethylene Oxide	D		
Ethyl Acetate	D	100%%	
Ethyl Alcohol	A	96%%	
Ethylene Chloride	D	100%%	
Food Oil	A		
Formaldehyde (aqueous)	A	40%%	
Formic Acid	A	10%%	
Frost Protection Agent	A		
Fuel (aromatic free)	A		
Glycerin	A	100%%	
Glycol	A	100%%	
Heating Oil	A		
Heptane	A	100%%	
Hydrochloric Acid	A	10%%	
Hydrochloric Acid (concentrated)	A	conc.%	
Hydrofluoric Acid	A	40%%	
Hydrogen Peroxide	A	10%%	
Hydrogen Sulfide (aqueous solution)	A		
Isopropyl Alcohol	A	100%%	
Linseed Oil	A		
Mercurochrome	B		
Methyl Alcohol	A	100%%	
Methyl Ethyl Ketone (MEK)	D	100%%	
Methylene Chloride	D	100%%	
Milk	A		

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
Mineral Oils (aromatic free)	A		
Nitric Acid	A	10%%	
Nitric Acid	A	50%%	
Nitrobenzene	D		
Oxalic Acid	A		
Ozone Gas	A	≤ 0.5 ppm%	
Paraffine Oil	A	100%%	
Perchloroethylene	D		
Petroleum	A	100%%	
Petroleum Ether	A	100%%	
Phenol (aqueous)	B	ca. 9%%	
Phosphoric Acid	A	50%%	
Potassium Hydroxide liquor	A	50%%	
Premium Fuel	D		
Propyl Alcohol	A		
Pyridine	D		
Silicone Oil	A		
Sodium Carbonate (aqueous)	A		
Sodium Chloride (aqueous)	A		
Sodium Hydrogen Sulfite	A		
Sodium Hydroxide liquor	A	15%%	
Sodium Hydroxide liquor	A	60%%	
Sodium Nitrate (aqueous)	A		
Sodium Thiosulfate	A		
Sulfuric Acid	A	96%%	
Tetrahydrofuran (THF)	D	100%%	
Toluene	D	100%%	
Transformer Oil	A		
Trichloroethylene	D	100%%	



PlastShop.se
Söderleden 22
587 31 Linköping
Sverige

KEMIKALE	BETYG	KONCENTRATION	TEMPERATUR
Vinegar (standard)	A	5 - 10%%	
Water	A		
Xylene	D		

PlastShop.se
Söderleden 22 , Linköping , Sverige

Tel: +46 13 328 94 00
info@plastshop.se
<https://plastshop.se>

Informationen i detta dokument baseras på aktuell kunskap och erfarenhet. Värden kan variera beroende på bearbetning och användningsförhållanden. Alla uppgifter utan garanti.